Xtal2DoS: Attention-based Crystal to Sequence Learning for Density of States Prediction

Abstract

Modern machine learning techniques have been extensively applied to the materials science, especially for property prediction tasks. A majority of these methods address the scalar property predictions, while more challenging spectral properties remain less emphasized. We formulate a crystal-to-sequence learning task and propose a novel attention-based learning method, Xtal2DoS, which decodes the sequential representation of material density of states (DoS) properties by incorporating the learned atomic embeddings through attention networks. Experiments show Xtal2DoS is faster than the existing models, and consistently outperforms other state-of-the-art methods on four metrics for two fundamental spectral properties, phonon and electronic DoS.

1 Introduction

Machine learning for materials discovery has risen to prominence recently, with impressive applications to materials' property predictions Liu et al. [2017], Schmidt et al. [2019]. While the performance greatly exceeds the existing models, most of the achievements are confined to individual scalar quantities Xie and Grossman [2018], Isayev et al. [2017], De Jong et al. [2016], Zhuo et al. [2018]. For conventional machine learning models, some other structured properties are often hard to deal with, for example spectral properties Eismann [2012]. Two fundamental spectral properties are phonon density of states (phDoS) Osborn et al. [2001] and electronic density of states (eDoS) Heremans et al. [2008]. In a given frequency interval, phDoS describes the number of phonon modes if the density of wave vectors in the Brillouin zone is homogeneously distributed. The phonon density of states is typically normalized to one Parlinski [2010]. Similarly, eDoS depicts the number of different states at a particular energy level that electrons are allowed to occupy (namely, the number of electron states per unit volume per unit energy) Omar [1975]. Mathematically, the density of states can be regarded as a sequence depicting the fundamental characteristics of particles. Each crystalline material is associated with unique density of states (phDoS, eDoS). The goal of density of states prediction is to estimate this sequence given an input structure.

There are two challenges in this sequence prediction problem. First, the input crystals are 3D structures, which are very different from typical machine learning formats (i.e., vectors or matrices). Featurizing the crystal structures is the cornerstone of the whole learning process. If useful information cannot be extracted effectively, the follow-up predictions would be severely hampered. Essentially, each crystal structure is a collection of atoms. Each atomic site contains a specific element, and these sites can be seen as nodes on a graph. Atoms also have interactions with each other Martin [2020]. Close atoms often have strong bonds. These bonds can be represented by the connecting edges on the

$$D(E) = N(E)/V$$

Figure 1: An illustration of predicting eDoS from the crystal structure for material *CsF*.

graph Xie and Grossman [2018]. Conventional CNN Krizhevsky et al. [2012] and RNN Hochreiter and Schmidhuber [1997] are not applicable to graphs, while graph neural networks Hamilton et al. [2017] are specifically designed for such structures. The pioneering work applying GNN networks to materials property prediction was CGCNN Xie and Grossman [2018], where the crystal unit cell was formalized as a graph with atoms as nodes and bonds as edges. MEGNet Chen et al. [2019] further introduced a global state to add extra features like temperature, pressure, and entropy. More recently, GATGNN Louis et al. [2020] suggested using an attention mechanism to capture the global crystal structure beyond the local atomic environments. In GATGNN, the local augmented graph-attention layers encode the properties of local environments for each atom to obtain an abstract feature, and a global attention layer aggregates these atomic vectors by weighted averaging to produce the global feature vector for prediction. This exploitation of structure markedly facilitated feature extraction from the crystalline systems, and built an extensible foundation for various predictions.

The second challenge in sequence prediction is the target format. Works like GATGNN focused on the prediction of scalar properties such as formation energies, band gaps and elastic moduli. The performance of these models degrades when applied to spectral properties like eDoS and phDoS Kong et al. [2022]. The simplest way to adapt the previous methods to predict sequences is to expand the last layer to output multiple values instead of a single value. The general idea is similar to predicting multiple scalar properties simultaneously. However, such parallel prediction overlooks the sequential nature of the target DoS. The smoothness property cannot be enforced onto the predicted targets either. Mat2Spec Kong et al. [2022] observes this flaw and re-formulates the problem as a multi-target regression task. Mat2Spec keeps the framework of expanding the last layer to output more values, but additionally uses contrastive learning Henaff [2020] and a probabilistic variational autoencoder Doersch [2016] to model the correlations among different locations of the sequence.

In this work, we introduce Crystal-to-DoS (Xtal2DoS) learning, to improve both the graph encoding and the sequence decoding for phDoS and eDoS predictions. First, we inherit the general framework of GATGNN and employ graph attention networks (GAT) Veličković et al. [2017] to learn both the local and global attention. Second, we adopt the attention-based transformer to decode the target sequence Vaswani et al. [2017]. The transformer reads the one-hot position embedding together with the global crystal representation, and decodes left-to-right auto-regressively. Differing from the multi-target regression perspective, Xtal2DoS takes the sequence-to-sequence (seq2seq) learning perspective. In seq2seq, the decoding process incorporates both self-attention and source-attention. Self-attention retrieves the historical memory from the previous steps, and source-attention derives the similarity between the decoding sequence and the input sequence. In this DoS prediction task, the input is a graph rather than a sequence, so the source-attention attends each position with all the atom embeddings. The resulting model, Xtal2DoS, thus improves both the encoding and decoding over prior models, for this graph-to-sequence learning problem. Experimental results show our method can outperform the existing state-of-the-art models on all four evaluation metrics by over 15% on average for phDoS, and over 4% on average for eDoS.

2 Crystal-to-DoS Learning

2.1 Problem Formulation

The input crystal material x is denoted as a graph $G_x = (V, E)$. $V = \{u_i\}_{i=1}^n$ is the collection of n atoms where u_i is an atom embedding learnt from CGCNN. $E = \{e_{ij}\}_{1 \leq i,j \leq n}$ denotes the bonds connecting atoms. e_{ij} depicts the distance between two atoms i, j. For a crystalline system, the crystal structure repeats in the 3D space and each atom has a 3D coordinate. Though theoretically, each atom has connections with any other atom, for simplicity and generality, we choose n_{max_nbr} neighbors to be the upper bound for the number of neighbors of each atom. In other words, the sum of each row or column of G_x's adjacency matrix is smaller than or equal to n_{max_nbr}. Our goal is to predict y for each x. y is the desired density of states (phDoS or eDoS), with length l_y. $l_y = 51$ for phDoS and $l_y = 128$ for eDoS. l is predefined for each type of DoS. The learnt model maps x to y ($f : x \to y$). Figure 1 presents an example (caesium fluoride , *CsF*) of DoS prediction.

2.2 Graph Attention Encoder

As the prototype of GAT, graph convolutional network (GCN) Kipf and Welling [2016] combines the local graph structure and node-level features to yield impressive node predictions. However, the feature aggregation of GCN depends on structure and is mostly linear, constraining effectiveness of message passing on the graph. In GCN, a graph convolution operation can be written as

$$h_i^{l+1} = \sigma(\sum_{j \in N(i)} \frac{1}{c_{ij}} W^l h_j^l) \tag{1}$$

$\sigma(\cdot)$ is a non-linear activation function. W_l is the feature transformation matrix in the l-th layer. h_i^l is the latent node embedding for node i in the l-th layer, with $h_i^0 = u_i$. $c_{ij} = \sqrt{|N(i)||N(j)|}$ is a normalization constant and $N(i)$ is the set of node i's neighbors.

In Xtal2DoS, we use a variant of GAT, *UniMP* Shi et al. [2020], to encode the crystalline graph. Compared to GAT, UniMP adds support for edge features. For each layer in UniMP, h_i^l is first linearly transformed to queries, keys and values

$$q_i^l = W_q^l h_i^l + b_q^l, \qquad k_i^l = W_k^l h_i^l + b_k^l, \qquad v_i^l = W_v^l h_i^l + b_v^l. \tag{2}$$

Similarly, we also transform the edge features between node i and node j

$$g_{ij} = W_e e_{ij} + b_e. \tag{3}$$

The edge feature transformation is not layer-dependent and W_e, b_e are shared for all edges. The attention coefficients are then computed as follows

$$\alpha_{ij}^l = \frac{\langle q_i^l, \ k_j^l + g_{ij} \rangle}{\sum_{p \in N(i)} \langle q_i^l, \ k_p^l + g_{ip} \rangle} \tag{4}$$

where $\langle q, k \rangle = \exp(\frac{q^T k}{\sqrt{d}})$ and d is the dimensionality of q_i^l, k_i^l or v_i^l. Afterwards, the embeddings from neighbors are aggregated, together with the edge embeddings, weighted by attention scores

$$\hat{h}_i^{l+1} = \sum_{j \in N(i)} \alpha_{ij}^l \cdot (v_j^l + e_{ij}). \tag{5}$$

From Eq. 1 and Eq. 5, GAT considers similarity scores and edge information when performing the aggregation to gain more expressiveness.

Finally, motivated by the success of residual neural networks He et al. [2016], UniMP appends a gated residual connection before passing $\hat{h}_i^{l+1}$ to the next layer

$$\begin{aligned} r_i^l &= W_r^l h_i^l + b_r^l, \qquad \beta_i^l = \text{sigmoid}(a^l [\hat{h}_i^{l+1} ; r_i^l ; \hat{h}_i^{l+1} - r_i^l]) \\ h_i^{l+1} &= \sigma(f_{LN}((1 - \beta_i^l) \hat{h}_i^{l+1} + \beta_i^l r_i^l)) \end{aligned} \tag{6}$$

where ; denotes concatenation, a^l is the learnable weight parameter, and f_{LN} represents the layer norm. Note that for the last layer of UniMP, $\sigma(\cdot)$ and f_{LN} are skipped.

(a) The global feature vector is fed into RNN as the initial state. The decoding unrolls step by step.

(b) Chunk RNN decoder is an RNN decoder that predicts a segment instead of a single value at each step.

Figure 2: Vanilla RNN, chunk RNN (without attentions).

Figure 3: Adding an attention mechanism to the chunk RNN decoder.

Figure 4: Fully attention-based transformer decoding for DoS prediction. All the recurrent components are replaced with self-attention.

2.3 Sequential Decoding

GAT learns embeddings for each node, h_i^L, if there are L layers in total. GATGNN and Mat2Spec simply take the average of all the embeddings as the global feature vector

$$h_x = \frac{1}{n} \sum_{i=1}^{n} h_i^L \tag{7}$$

Then the global feature vector is used to decode the target DoS, using MLP or VAE.

We compared various sequence models including RNN and transformer for decoding. By default, we used the GRU model for RNN.

RNN Figure 2a sketches the RNN decoding of the GAT-encoded crystal. RNN is naturally suitable for sequence decoding. It reads the global feature vector as the cell state and a special $\langle start \rangle$ symbol to indicate the start of the decoding. The output at each step is also the input for the next step. However, RNN is criticized for lacking long-term memory Zhao et al. [2020]. When we decode the last step (y_{127}), the memory of the first step (y_0) is probably degraded. This might hurt the prediction quality for long sequences. Another drawback of RNN is the speed. Each step has to wait for the previous output, and thus the decoding process could take a very long time.

Chunk RNN Figure 2b gives an overview of a chunk RNN, which is a simple RNN variant. Chunk RNN predicts a segment rather than a single value at each step. The benefit is that the decoding time could be greatly shortened. For instance, on eDoS, if the segment length is 32, then sequence length can be reduced from 128 to 4. On the other hand, each segment still waits for the generation of the previous segment, and longer segments harm the accuracy gradually.

Chunk RNN + Attention To compensate for the performance degradation brought by chunk RNN, we further introduce the attention mechanism into the sequence model (Figure 3). The attention module directly attends to the latent sequence states with the atom embeddings. The latent states can take specific atoms into consideration and build more fine-grained correlations. In practice, we also find including the attention module boosts the evaluation results.

Transformer Given that we have already introduced the attention mechanism, it is intuitive to completely drop the recurrent framework and embrace the fully attentional transformer Vaswani

et al. [2017]. The input at each step is the concatenation of the positional embeddings and the global feature vector. A positional embedding is simply a one-hot vector of length l_y indicating the index of the current step. The global feature vector h_x additionally provides the global context for decoding. Formally, let $z_i = [s_i \; ; \; h_x]$ where s_i is the one-hot position embedding with length l_y. z_i is the initial state for the first self-attention layer. As in UniMP, we derive collections of queries, keys and values for the hidden states of each self-attention layer, denoted by Q, K, and V, respectively.

Transformer adopts dot-product attention to calculate the outputs

$$\text{Attention}(Q, K, V) = \text{softmax}(QK^T/\sqrt{d})\, V \tag{8}$$

where d is the latent dimensionality. Multiple sets of Q, K, and V matrices can be learned, and each set is known as a head. Multiple heads (multi-head) can give self-attention greater power of discrimination. The outputs of all the heads are concatenated, layer-normalized and decoded through a fully connected feed-forward network. A more detailed depiction can be found in Vaswani et al. [2017].

During the decoding phase, each attention layer also computes the source-attention between the output states and the input atom nodes. If we denote the queries, keys, values in decoding as $Q_{dec}, K_{dec}, V_{dec}$, and the ones from the input graph encoding as $Q_{enc}, K_{dec}, V_{dec}$, we have

$$
\begin{aligned}
\text{Self-Attention}(Q_{dec}, K_{dec}, V_{dec}) &= \text{softmax}(\frac{Q_{dec}K_{dec}^T}{\sqrt{d}})V_{dec}, \\
\text{Source-Attention}(Q_{dec}, K_{enc}, V_{enc}) &= \text{softmax}(\frac{Q_{dec}K_{enc}^T}{\sqrt{d}})V_{enc},
\end{aligned}
\tag{9}
$$

for the sequential decoding. Source-attention usually happens after self-attention. Furthermore, the transformer model adds masking to prevent the current positions from attending to the future positions, to prevent leftward information flow in the decoder, and to preserve the auto-regressive property, ensuring each decoded state only knows the history but not the future. The final generated length-l_y sequence $\hat{y}$ is compared with the ground-truth y through Kullback–Leibler divergence (KL-div) Kullback [1997] or its generalized version, *Bregman Divergence* (BD) Bregman [1967], resulting in the loss term, $\mathcal{L} = D_{KL}(y \,\|\, \hat{y})$. We chose KL-div and BD because they are more suitable than other measures for data containing peaks, which are ubiquitous in DoS.

Our model is a synergistic combination of a GAT (UniMP) encoder and a transformer decoder. The whole model is entirely based on attentions on graphs and sequences. Figure 4 illustrates the main idea of Xtal2DoS.

3 Related Works

Learning for 3D structures has been a long-standing problem. In materials discovery, two atomic systems can be exactly the same even though the coordinates are totally different in the 3D space if they can be transformed to one another through translation, rotation or inversion. For standard machine learning models, it is very hard to capture such invariance and symmetry Cohen and Welling [2016]. There are in general three strategies to address the concern.

First, the same models can be trained using more data Shorten and Khoshgoftaar [2019]. The structured inputs can be randomly transformed without changing the labels. Some prior works successfully applied data augmentation to exploring materials design spaces Kim et al. [2021]. On the other hand, in materials science, even with augmentation, it is not easy for machine learning models to comprehend the crystalline system, let alone the data collection and augmentation require enormous domain knowledge and expert effort Schmidt et al. [2019].

Second, rather than expanding the scale on the dataset side, some researchers have explored the possibility of enforcing the invariance or equivariance inside the model. This kind of model handles the coordinates directly and are often called equivariant neural networks Satorras et al. [2021], Du et al. [2022]. One notable model for materials science applications is E3NN Chen et al. [2021].

173 E3NN performs training based on radial functions and spherical harmonics Esteves et al. [2018].
174 Intuitively, E3NN represents the atoms with the 3D coordinates, mass and velocity, and tells the
175 equivariant convolutional filters how the crystals might transform. Thus, E3NN can capture the full
176 crystal symmetry, while reducing training set sample complexity. However, radial functions and
177 spherical harmonics may limit the expressiveness of the model. In some scenarios where the data is
178 abundant, E3NN's benefits might become marginal.

179 Third, it is often helpful to pre-process the data for simplicity Kumar [2018]. Instead of using the
180 coordinates, we can re-format the crystals to graphs by retaining only the atoms and the bonds
181 between them. Some of the structure information is lost from the input, such as the lattice angles,
182 but this could also reduce the risk of overfitting. Once the inputs are converted to graphs, mature
183 graph neural network techniques Wu et al. [2020] can be applied. A representative work is GATGNN
184 Louis et al. [2020]. GATGNN is one of the primary methods to encode the atom embeddings and
185 extract the global feature vector. It still leads in the performance of many scalar property prediction
186 tasks including absolute energy, Fermi energy, band gap and Poisson-ratio. Nevertheless, in sequence
187 property predictions, its performance degrades significantly Kong et al. [2022]. Mat2Spec Kong et al.
188 [2022] uses the same graph encoder as GATGNN, but improves the decoder. GATGNN only uses
189 an MLP, which is incapable of sequence decoding. Mat2Spec not only aligns the inputs and targets
190 in a latent multivariate Gaussian space, but also learns an embedding for each energy level through
191 contrastive learning. Mat2Spec views the DoS prediction as a multi-target regression problem, yet
192 ignores the sequential structure of DoS. Besides, Mat2Spec simply deepens the MLP decoder and
193 plugs contrastive modules into the decoder, while sequence modeling is cleaner and simpler.

194 Xtal2DoS follows the design of GATGNN and Mat2Spec because the graph encoding is shown to
195 outperform the coordinate encoding Kong et al. [2022]. On top of the existing designs, Xtal2DoS
196 further replaces GAT encoder with a more advanced variant, UniMP, and replaces the decoder with a
197 powerful sequence model, transformer. Evaluation results and ablation studies prove the effectiveness
198 and efficiency of our introduced model.

4 Experiments on DoS Prediction

200 We validate the performance of Xtal2DoS on two datasets, phDoS and eDoS. The task of directly
201 predicting phDoS in crystalline solids from atomic species and positions was first proposed in E3NN
202 Chen et al. [2021]. We also include a new version of E3NN, denoted by E3NN-new [1]. phDoS is
203 normalized to 1 since phDoS gives the number of modes per unit frequency per unit volume of
204 real space and is essentially a distribution. phDoS is critical for calculating properties such as the
205 average phonon frequency and the heat capacity at 300K. The analogous task of predicting eDoS for
206 nonmagnetic materials was proposed in Kong et al. [2022]. eDoS is the same as phDoS except that it
207 depicts electrons. Materials scientists are interested in a small energy range between -4 to 4 eV with
208 respect to band edges with 63 meV intervals, including both unoccupied and occupied states. Fermi
209 energy and band edges are all set to 0 eV on this energy grid. Predicting eDoS accurately can be very
210 valuable to bandgap energy estimation. Both phDoS and eDoS are continuous functions in nature.
211 We sample 51 points on phDoS and 128 points on eDoS spanning the frequency or energy range. In
212 other words, $l_y = 51$ for phDoS and $l_y = 128$ for eDoS.

4.1 Evaluation Metrics

214 Four metrics are adopted for evaluation: coefficient of determination (R^2), mean absolute error
215 (MAE), mean squared error (MSE) and Wasserstein distance (WD).

216 R^2 measures the proportion of the variation in the ground-truth targets y that is predictable from the
217 predictions $\hat{y}$,

$$R^2 = 1 - \frac{\sum_{i=1}^{l_y}(y_i - \hat{y}_i)^2}{\sum_{i=1}^{l_y}(y_i - \bar{y})^2} \tag{10}$$

---

[1]https://docs.e3nn.org/en/stable/api/nn/models/gate_points_2101.html

model	$R^2\uparrow$	MAE $\downarrow$	MSE $\downarrow$	WD $\downarrow$	model	$R^2\uparrow$	MAE $\downarrow$	MSE $\downarrow$	WD $\downarrow$
E3NN	0.560	0.0937	0.0365	0.1217	E3NN	0.410	4.8968	99.852	0.467
E3NN-new	0.605	0.0737	0.0208	0.0680	E3NN-new	0.555	3.9190	74.949	0.233
GATGNN	0.457	0.0869	0.0426	0.1376	GATGNN	0.492	4.2965	85.555	0.285
E3NN2DoS	0.622	0.0704	0.0199	0.0740	E3NN2DoS	0.552	3.8900	75.453	0.236
Mat2Spec	0.620	0.0782	0.0231	0.0736	Mat2Spec	0.545	3.8939	76.624	0.230
Xtal2DoS	**0.683**	**0.0642**	**0.0166**	**0.0631**	Xtal2DoS	**0.577**	**3.7845**	**71.213**	**0.218**
improve	9.81%	8.81%	16.58%	7.21%	improve	3.96%	2.71%	4.98%	5.22%

Table 1: The evaluation results of four metrics on phDoS.   Table 2: The evaluation results of four metrics on eDoS.

where $\bar{y} = \frac{1}{l_y}\sum_i y_i$. In the best case when y and $\hat{y}$ match exactly, R^2 would reach the maximum possible value, 1. If $y_i = \bar{y}$, $R^2 = 0$. Note that R^2 score can be negative if the predictions are worse.

MAE and MSE are standard metrics for regression. We also adopt them for evaluation:

$$\text{MAE} = \frac{1}{l_y}\sum_{i=1}^{l_y}|y_i - \hat{y}_i|, \qquad \text{MSE} \;\; = \frac{1}{l_y}\sum_{i=1}^{l_y}(y_i - \hat{y}_i)^2 \tag{11}$$

Wasserstein distance is another metric defined between probability distributions. If we view the two distributions as two piles of earth, WD is the minimum amount of dirt to move in order to turn one pile to be the same as the other. Therefore, WD is also known as earth mover's distance. We define the WD as

$$\text{WD} = \int_{-\infty}^{+\infty}|P - Q| \tag{12}$$

for distributions p and q with cumulative distribution functions (CDF) P and Q, respectively. The continuous form of WD can also be adapted for discrete cases.

4.2 Implementation

The graph encoder is built with PyTorch Geometric Fey and Lenssen [2019] modules. The encoder is composed of three GAT/UniMP layers, each followed by batch normalization Ioffe and Szegedy [2015] and a non-linear activation He et al. [2015]. The sequence decoder is a stack of six self-attention layers, where each layer has subsequent layer normalization and feed-forward layers. The whole model is trained with the Adam optimizer Kingma and Ba [2014], on Nvidia V100 GPU.

4.3 Prediction Results

Xtal2DoS is first evaluated on phDoS, compared with other state-of-the-art baselines, including E3NN, GATGNN, Mat2Spec and some of their variants. Among all the compared methods, Xtal2DoS gives the best numbers. On R^2, MAE, MSE and WD, the relative improvements over the best compared baseline are as large as 9.81%, 8.81%, 16.58%, 7.21%, respectively. The average improvement is 10.60%.

Table 2 shows the performance gain achieved by Xtal2DoS over other competitive baselines on the more challenging eDoS dataset. Xtal2DoS outperformed the best baseline on the four metrics by 3.96%, 2.71%, 4.98%, 5.22% respectively. The average improvement is 4.22%, which is a noticeable increment especially when the training speed is faster (see section 4.6).

4.4 Ablation Study

To validate the neural module selection of Xtal2DoS, we further compare the performance of RNN, RNN+attention, Chunk RNN+attention, and the transformer (Xtal2DoS). We use the same four metrics to compare these settings. In Table 3 and 4, transformers always dominate other RNN-based models on all the metrics. The improvements shown in the last row indicate the comparison between Xtal2DoS and the best compared model (usually Chunk RNN+Attn).

model	$R^2\uparrow$	MAE↓	MSE↓	WD↓
RNN	0.663	0.00794	0.000245	0.0797
RNN+Attn	0.668	0.00726	0.000241	0.0664
Chunk RNN+Attn	0.693	0.00720	0.000223	0.0656
Xtal2DoS	0.732	0.00677	0.000194	0.0634
improve	5.63%	5.97%	13.00%	3.35%

Table 3: Ablation study on phDoS.

model	$R^2\uparrow$	MAE↓	MSE↓	WD↓
Chunk RNN+Attn	0.558	3.9125	75.013	0.221
Xtal2DoS	0.575	3.7353	71.566	0.210
improve	3.05%	4.53%	4.60%	4.98%

Table 4: Ablation study on eDoS.

model	E3NN	Mat2Spec	RNN	RNN+Attn	Chunk RNN+Attn	**Xtal2DoS**
Time per epoch (s)	31	33	54	69	42	**11**

Table 5: The training time for Mat2Spec, RNN-based sequence models and Xtal2DoS. For fair comparison, we illustrate the training cost for each epoch in seconds.

4.5 Qualitative Results

We also show some qualitative results on both phDoS and eDoS in Figure 5 and 6 (in Appendix). Both figures demonstrate the accuracy of our predictions. The red and blue lines are always closely correlated.

4.6 Training Speed

One major advantage of transformer models is parallelism. Unlike RNNs where each step has to wait for the previous output, transformer computes the outputs at all the steps simultaneously and enforces auto-regressiveness through masking. These operations can be performed in matrix form, taking advantage of powerful GPUs, and thus substantially reduce the training cost. Table 5 shows the training time per epoch for Mat2Spec, RNN-based sequence models and Xtal2DoS. Mat2Spec does not involve any sequential model and generates outputs through MLP, so it is faster than any RNN-based sequence decoder model. Mat2Spec instead integrates probabilistic sampling and contrastive learning, so it is not surprising that it takes more time than Xtal2DoS. Unsurprisingly, RNN trains more than 50% slower than Mat2Spec. Adding the attention module further prolongs the time cost. RNN+Attention doubles the training cost compared with Mat2Spec. This also motivated us to attempt chunk RNN. As a result, chunk RNN+Attention can complete a training epoch faster than RNN and RNN+Attention, but is still slower than Mat2Spec. Xtal2DoS is the fastest method among all these models. It only takes one third of Mat2Spec's training time, one fifth of RNN's training time, and one fourth of chunk RNN+Attention's training time. Xtal2DoS excels at speed because of its parallel design and its succinct structure to avoid extra neural module. Faster models are often more advantageous in training, tuning and deploying.

5 Conclusion

In this work, we introduce a novel graph-to-sequence learning framework, *Xtal2DoS*, for predicting the spectral properties of materials, *phDoS* and *eDoS*, from the input crystalline structures. Our model adopts an improved graph attention network (to handle edges) as the graph encoder, and a transformer as the decoder for sequential decoding. Xtal2DoS is fully attentional and captures all the atom-atom, atom-sequence and step-step correlations. Therefore, it considerably exceeds other existing state-of-the-art baselines, in quantitative evaluation metrics, qualitative matching results and training speed.

References

Yue Liu, Tianlu Zhao, Wangwei Ju, and Siqi Shi. Materials discovery and design using machine learning. *Journal of Materiomics*, 3(3):159–177, 2017.

Jonathan Schmidt, Mário RG Marques, Silvana Botti, and Miguel AL Marques. Recent advances and applications of machine learning in solid-state materials science. *npj Computational Materials*, 5 (1):1–36, 2019.

Tian Xie and Jeffrey C Grossman. Crystal graph convolutional neural networks for an accurate and interpretable prediction of material properties. *Physical review letters*, 120(14):145301, 2018.

Olexandr Isayev, Corey Oses, Cormac Toher, Eric Gossett, Stefano Curtarolo, and Alexander Tropsha. Universal fragment descriptors for predicting properties of inorganic crystals. *Nature communications*, 8(1):1–12, 2017.

Maarten De Jong, Wei Chen, Randy Notestine, Kristin Persson, Gerbrand Ceder, Anubhav Jain, Mark Asta, and Anthony Gamst. A statistical learning framework for materials science: application to elastic moduli of k-nary inorganic polycrystalline compounds. *Scientific reports*, 6(1):1–11, 2016.

Ya Zhuo, Aria Mansouri Tehrani, and Jakoah Brgoch. Predicting the band gaps of inorganic solids by machine learning. *The journal of physical chemistry letters*, 9(7):1668–1673, 2018.

MT Eismann. Spectral properties of materials'. *Hyperspectral Remote Sensing*, pages 133–198, 2012.

R Osborn, EA Goremychkin, AI Kolesnikov, and DG Hinks. Phonon density of states in mgb 2. *Physical Review Letters*, 87(1):017005, 2001.

Joseph P Heremans, Vladimir Jovovic, Eric S Toberer, Ali Saramat, Ken Kurosaki, Anek Charoenphakdee, Shinsuke Yamanaka, and G Jeffrey Snyder. Enhancement of thermoelectric efficiency in pbte by distortion of the electronic density of states. *Science*, 321(5888):554–557, 2008.

Krzysztof Parlinski. Computing for materials, 2010.

M Ali Omar. *Elementary solid state physics: principles and applications*. Pearson Education India, 1975.

Richard M Martin. *Electronic structure: basic theory and practical methods*. Cambridge university press, 2020.

Alex Krizhevsky, Ilya Sutskever, and Geoffrey E Hinton. Imagenet classification with deep convolutional neural networks. *Advances in neural information processing systems*, 25, 2012.

Sepp Hochreiter and Jürgen Schmidhuber. Long short-term memory. *Neural computation*, 9(8): 1735–1780, 1997.

Will Hamilton et al. Inductive representation learning on large graphs. In *Advances in neural information processing systems*, pages 1024–1034, 2017.

Chi Chen, Weike Ye, Yunxing Zuo, Chen Zheng, and Shyue Ping Ong. Graph networks as a universal machine learning framework for molecules and crystals. *Chemistry of Materials*, 31(9):3564–3572, 2019.

Steph-Yves Louis, Yong Zhao, Alireza Nasiri, Xiran Wang, Yuqi Song, Fei Liu, and Jianjun Hu. Graph convolutional neural networks with global attention for improved materials property prediction. *Physical Chemistry Chemical Physics*, 22(32):18141–18148, 2020.

Shufeng Kong, Francesco Ricci, Dan Guevarra, Jeffrey B Neaton, Carla P Gomes, and John M Gregoire. Density of states prediction for materials discovery via contrastive learning from probabilistic embeddings. *Nature communications*, 13(1):1–12, 2022.

Olivier Henaff. Data-efficient image recognition with contrastive predictive coding. In *International conference on machine learning*, pages 4182–4192. PMLR, 2020.

Carl Doersch. Tutorial on variational autoencoders. *arXiv preprint arXiv:1606.05908*, 2016.

Petar Veličković, Guillem Cucurull, Arantxa Casanova, Adriana Romero, Pietro Lio, and Yoshua Bengio. Graph attention networks. *arXiv preprint arXiv:1710.10903*, 2017.

Ashish Vaswani, Noam Shazeer, Niki Parmar, Jakob Uszkoreit, Llion Jones, Aidan N Gomez, Łukasz Kaiser, and Illia Polosukhin. Attention is all you need. *Advances in neural information processing systems*, 30, 2017.

Thomas N Kipf and Max Welling. Semi-supervised classification with graph convolutional networks. *arXiv preprint arXiv:1609.02907*, 2016.

Yunsheng Shi, Zhengjie Huang, Shikun Feng, Hui Zhong, Wenjin Wang, and Yu Sun. Masked label prediction: Unified message passing model for semi-supervised classification. *arXiv preprint arXiv:2009.03509*, 2020.

Kaiming He, Xiangyu Zhang, Shaoqing Ren, and Jian Sun. Deep residual learning for image recognition. In *Proceedings of the IEEE conference on computer vision and pattern recognition*, pages 770–778, 2016.

Jingyu Zhao, Feiqing Huang, Jia Lv, Yanjie Duan, Zhen Qin, Guodong Li, and Guangjian Tian. Do rnn and lstm have long memory? In *International Conference on Machine Learning*, pages 11365–11375. PMLR, 2020.

Solomon Kullback. *Information theory and statistics*. Courier Corporation, 1997.

Lev M Bregman. The relaxation method of finding the common point of convex sets and its application to the solution of problems in convex programming. *USSR computational mathematics and mathematical physics*, 7(3):200–217, 1967.

Taco Cohen and Max Welling. Group equivariant convolutional networks. In *International conference on machine learning*, pages 2990–2999. PMLR, 2016.

Connor Shorten and Taghi M Khoshgoftaar. A survey on image data augmentation for deep learning. *Journal of big data*, 6(1):1–48, 2019.

Yongtae Kim, Youngsoo Kim, Charles Yang, Kundo Park, Grace X Gu, and Seunghwa Ryu. Deep learning framework for material design space exploration using active transfer learning and data augmentation. *npj Computational Materials*, 7(1):1–7, 2021.

Vıctor Garcia Satorras, Emiel Hoogeboom, and Max Welling. E (n) equivariant graph neural networks. In *International conference on machine learning*, pages 9323–9332. PMLR, 2021.

Weitao Du, He Zhang, Yuanqi Du, Qi Meng, Wei Chen, Nanning Zheng, Bin Shao, and Tie-Yan Liu. Se (3) equivariant graph neural networks with complete local frames. In *International Conference on Machine Learning*, pages 5583–5608. PMLR, 2022.

Zhantao Chen, Nina Andrejevic, Tess Smidt, Zhiwei Ding, Qian Xu, Yen-Ting Chi, Quynh T Nguyen, Ahmet Alatas, Jing Kong, and Mingda Li. Direct prediction of phonon density of states with euclidean neural networks. *Advanced Science*, 8(12):2004214, 2021.

Carlos Esteves, Christine Allen-Blanchette, Ameesh Makadia, and Kostas Daniilidis. Learning so (3) equivariant representations with spherical cnns. In *Proceedings of the European Conference on Computer Vision (ECCV)*, pages 52–68, 2018.

Dhairya Kumar. Introduction to data preprocessing in machine learning, 2018.

Zonghan Wu, Shirui Pan, Fengwen Chen, Guodong Long, Chengqi Zhang, and S Yu Philip. A comprehensive survey on graph neural networks. *IEEE transactions on neural networks and learning systems*, 32(1):4–24, 2020.

366 Matthias Fey and Jan Eric Lenssen. Fast graph representation learning with pytorch geometric. *arXiv*
367   *preprint arXiv:1903.02428*, 2019.

368 Sergey Ioffe and Christian Szegedy. Batch normalization: Accelerating deep network training by
369   reducing internal covariate shift. In *International conference on machine learning*, pages 448–456.
370   PMLR, 2015.

371 Kaiming He, Xiangyu Zhang, Shaoqing Ren, and Jian Sun. Delving deep into rectifiers: Surpassing
372   human-level performance on imagenet classification. In *Proceedings of the IEEE international*
373   *conference on computer vision*, pages 1026–1034, 2015.

374 Diederik P Kingma and Jimmy Ba. Adam: A method for stochastic optimization. *arXiv preprint*
375   *arXiv:1412.6980*, 2014.

 # A   Qualitative Results

Figure 5: Comparison of the phDoS predictions and ground-truth labels on some crystalline systems. The red line denotes the prediction and the blue line denotes the ground-truth.

Figure 6: The comparison between the eDoS predictions and ground-truth labels on some crystalline systems. The red line denotes the prediction and the blue line denotes the ground-truth.