Recent developments and applications of the machine-learned moment tensor potentials

Nikita Rybin [1 2]   **Dmitry Fedorov** [1]   **Ivan Novikov** [3]   **Alexander Shapeev** [1 2]

[1]*Skolkovo Institute of Science and Technology, Skolkovo Innovation Center, Bolshoy boulevard 30, Moscow, 143026, Russian Federation* [2]*Digital Materials LLC, Odintsovo, Kutuzovskaya str. 4A Moscow region, 143001, Russian Federation* [3]*Faculty of Computer Science, HSE University, Moscow, Russia.* Correspondence to: Nikita Rybin n.rybin@skoltech.ru, n.rybin@digital-materials.ru, Alexander Shapeev a.shapeev@skoltech.ru.

1. Introduction

Machine learning interatomic potentials (MLIPs) have emerged as a powerful approach for atomistic simulations which allows one to perform large-scale simulations with high (usually near density-functional theory) accuracy. Among different MLIPs, the moment tensor potential model (MTP) [1] has established itself among the most accurate, efficient, and widely used [2].

This work highlights a number of recent methodological developments in MTP construction and also a number of applications, where MTPs were used to model materials. In particular, while initial MTP model, implemented in the MLIP-2 package, was purely local [3], recently, it was shown how to incorporate long-range interactions treatment in the MTP construction both in terms of dispersion interactions [4] and electostatics [5]. Another recent methodological development is related to the use of the low-rank matrix and tensor factorization to compress radial parameters of MLIPs (polynomial models such as MTP and atomic cluster expansion [6] were used as examples) to perform calculations more efficiently [7]. The MLIP-4 package [8] contains these methodological developments.

In the application part, we will demonstrate how we used MTPs to efficiently model lattice thermal conductivity of structures with defects [9] and of the peculiar Moiré lattices of hydrogenated graphene and boron nitride [10]. We applied MTPs to model the physical properties of liquid molecular electrolytes and have shown that active learning can be used to collect a training set, with which it is possible to treat long-range interactions explicitly [11]. We will also show how learning on atomic environments can be used to parameterize MTPs, which are then used for large-scale simulations of the Cs diffusion in amorphous and polycrystalline SiC [12]. MTPs can be also used to speed up crystal structure prediction process, and we will demonstrate how we do it for pharmaceutically-relevant molecular crystals and crystalline inorganic non-linear optical semiconductors [13, 14]. Using the former case, we will also highlight the importance of the treatment of nuclear quantum effects [15] and the proper choice [16] of the exchange-correlation functional used in the data set preparation step once the calculations are done in the scope of density-functional theory.

2. Related works and Results

2.1 Methodological developments

The number of parameters in the basis sets of MLIP influences both the size of the training dataset required and the computational speed. Consequently, compressing MLIPs by reducing the number of parameters is a promising route to more efficient simulations. We used low-rank matrix and tensor factorizations under fixed-rank constraints to achieve this compression [7] and have shown that such compression (even by 50%) still allowed us to perform proper polymorph's ranking using glycine as example (see Fig. 1).

Fig. 1: Relative stability of glycine polymorphs calculated using MTP of the 20th level with different compression algorithms and DFT. Averaging is done over 10 separately trained potentials for each model. See details in work [7].

To incorporate electrostatics, fixed per-element point charges offer a simple baseline, while more transferable models learn environment-dependent charges from reference data, and globally dependent charges address non-local effects [5]. Our MTP-QRd model employs fixed charges per-element to test if explicit electrostatics improves the modeling of EC/EMC mixtures [11], where local MLIPs have previously sufficed.

2.2 Applications.

The diffusion mechanism of Cs in high energy grain boundaries (HEGBs) of silicon carbide (SiC) remained unsolved due to the lack of reliable and computationally efficient interatomic potentials. We used MTP to resolve this problem. Simulations shown that

Cs diffuses following a cage-breaking mechanism [12]. Such calculations were done by utilizing active learning on atomic environments methodology, which is sketched in Fig. 2.

Fig. 2: Schematic representation of the learning on atomic environments procedure. See details in the work [12].

In the work [11], we demonstrated that active learning can automatically generate diverse training sets, enabling reliable molecular dynamics simulations of pure ethylene carbonate (EC), ethyl methyl carbonate (EMC), their mixtures, and $LiPF_6$ solutions. The resulting MTPs exhibit excellent transferability across various EC/EMC compositions, producing ionic conductivities within 11% mean deviations from experiments. In addition, we assessed the impact of explicitly incorporating electrostatics by extending MTP with a charge redistribution scheme. Our results show that this extended MTP achieves accuracy comparable to MTP for EC/EMC mixtures with fewer parameters and reproduces ionic conductivity with only a 6% mean deviation from experiment.

Fig. 3: Temperature dependence of the lattice thermal conductivity of the hydrogenated graphene and boron nitride.

In the works [10, 9] we have shown how MTPs can be used to effectively model temperature dependence of the lattice thermal conductivity (LTC) of complex compounds in the scope of Green-Kubo theory. In [9] we quantified the influence of different defects on the thermal conductivity of PbTe, whereas in [10] we evaluated LTC of complex Moiré lattices of the hydrogenated graphene and boron nitride. In the latter work it has been shown that anharmonic effects cause tremendous influence and should be taken into account to quantitatively estimate LTC of these compounds (see Fig. 3).

We are also going to discuss how path-integral molecular dynamics simulations can be performed with MTP [15] and how it can be used for proper molecular crystals structure prediction and ranking [13]. That said, we will also highlight how the proper DFT-based dataset should be constructed [16] for molecular crystals.

In summary, we are going to discuss recent methodological developments done with MTP model and recent applications where MTP showed its efficiency. In addition, we will discuss future work that should be done to generate MLIPs for more realistic matter simulations.

Acknowledgments

The work was supported by the grant for research centers in the field of AI provided by the Ministry of Economic Development of the Russian Federation in accordance with the agreement 000000C313925P4F0002 and the agreement with Skoltech №139-10-2025-033. This work was partially supported by the Basic Research Program at the HSE University, Russian Federation. Part of this work (low-rank MLIPs approximations) was partially supported by the Basic Research Program at the HSE University, Russian Federation.

References

[1] Alexander V. Shapeev. Moment tensor potentials: A class of systematically improvable interatomic potentials. *Multiscale Modeling & Simulation*, 14(3):1153–1173, 2016.

[2] Yunxing Zuo, Chi Chen, Xiangguo Li, Zhi Deng, Yiming Chen, Jörg Behler, Gábor Csányi, Alexander V Shapeev, Aidan P Thompson, Mitchell A Wood, et al. Performance and cost assessment of machine learning interatomic potentials. *The Journal of Physical Chemistry A*, 124(4):731–745, 2020.

[3] Ivan S Novikov, Konstantin Gubaev, Evgeny V Podryabinkin, and Alexander V Shapeev. The mlip package: moment tensor potentials with mpi and active learning. *Machine Learning: Science and Technology*, 2(2):025002, 2020.

[4] Olga Chalykh, Dmitry Korogod, Ivan S. Novikov, Max Hodapp, Nikita Rybin, and Alexander V. Shapeev. Moment tensor potential and equivariant tensor network potential with explicit dispersion interactions. *The Journal of Chemical Physics*, 163(13), October 2025.

[5] Dmitry Korogod, Olga Chalykh, Max Hodapp, Nikita Rybin, Ivan S. Novikov, and Alexander V. Shapeev. Incorporating coulomb interactions with fixed charges in moment tensor potentials and equivariant tensor network potentials, 2025.

[6] Ralf Drautz. Atomic cluster expansion for accurate and transferable interatomic potentials. *Physical Review B*, 99(1):014104, 2019.

[7] Igor Vorotnikov, Fedor Romashov, Nikita Rybin, Maxim Rakhuba, and Ivan S Novikov. Low-rank matrix and tensor approximations for compression of machine-learning interatomic potentials. *The Journal of Chemical Physics*, 163(24), 2025.

[8] Alexander Shapeev. Mlip-4, 2024.

[9] Ilya V Chepkasov, Aleksandra D Radina, Viktor S Baidyshev, Mikhail Polovinkin, Nikita Rybin, Alexander Shapeev, Artem A Krikorov, Artem R Oganov, Zinovi Dashevsky, Dmitry G Kvashnin, et al. Tuning of mechanical properties of doped pbte-based thermoelectric materials driven by intrinsic defects. *Journal of Materials Chemistry A*, 13(37):31170–31181, 2025.

[10] Rustam Arabov, Nikita Rybin, Victor Demin, Mikhail Polovinkin, Alexander Kvashnin, Leonid Chernozatonskii, and Alexander Shapeev. Tuning thermal conductivity and electron–phonon interactions in carbon and boron nitride moiré diamanes via twist angle manipulation. *Applied Surface Science*, 717:164801, 2026.

[11] Olga Chalykh, Mikhail Polovinkin, Dmitry Korogod, Nikita Rybin, and Alexander Shapeev. Active learning and explicit electrostatics enable accurate modeling of electrolytes. *arXiv preprint arXiv:2510.03479*, 2025.

[12] Jiaxuan Li, Nikita Rybin, Taowei Wang, Alexander Shapeev, Xiaotong Chen, and Bing Liu. Revealing the diffusion mechanism of cs in amorphous and polycrystalline sic by actively trained moment tensor potentials. *npj Computational Materials*, 2026.

[13] Nikita Rybin, Ivan S Novikov, and Alexander Shapeev. Accelerating structure prediction of molecular crystals using actively trained moment tensor potential. *Physical Chemistry Chemical Physics*, 27(10):5141–5148, 2025.

[14] Nikita Rybin, Ivan Kruglov, and Alexander Shapeev. Predicting novel non-linear optical materials using machine-learned interatomic potentials and evolutionary crystal structure prediction. *In Preparation*, 2026.

[15] A.A. Solovykh, N.E. Rybin, I.S. Novikov, and A.V. Shapeev. Path-integral molecular dynamics with actively-trained and universal machine learning force fields. *Computer Physics Communications*, 319:109902, 2026.

[16] Dmitry V Fedorov, Nikita E Rybin, Mikhail A Averyanov, Alexander V Shapeev, Artem R Oganov, and Carlo Nervi. Towards superior van der waals density functionals for molecular crystals. *arXiv preprint arXiv:2511.20738*, 2025.