`LithographyAgent`: Lithography Solvent Discovery using Neuro-Symbolic Search Agent

Jiangyu Chen [* 1 2]   Huawei Zhou [* 2]   Zhou Zhang [1 2]   Yuqiang Li [3]   Ruzhi Zhang [2]   Tianfan Fu [1 3]

Abstract

Scientific formulation discovery often unfolds under imperfect evaluators: wet-lab validation is expensive, design spaces are combinatorial, and available proxy scores only partially reflect downstream experimental performance. We study this challenge in lithography solvent design, a mixed discrete–continuous problem that requires selecting solvent components and optimizing their mixing ratios under explicit physicochemical constraints. We propose `LithographyAgent`, a diversity-aware neuro-symbolic search framework for solvent discovery under evaluator uncertainty. LLMs act as chemistry-informed hypothesis generators over discrete formulation topologies, while a differentiable physics-informed module refines continuous mixture ratios and enforces feasibility. To reduce premature collapse toward evaluator-preferred patterns, `LithographyAgent` combines sibling-aware local diversification with memory-driven global planning. Experiments show that `LithographyAgent` maintains full compliance with the explicit physicochemical constraints adopted in our framework and improves exploration diversity over score-centric baselines. Additional external baselines under the same physics optimizer show that stronger proxy optimization can select chemically implausible candidates: a surrogate-guided baseline obtains the highest Top-10 proxy score but zero Top-10 EHS pass rate across three seeds. Scoring and calibration diagnostics further show that LLM-based qualitative assessment is not a trivial restatement of the physics proxy, and that contin-uous optimizer outputs require ratio calibration before experimental use. Representative lithography validation provides CD-SEM measurements for successful candidates and qualitative failure analysis for additional candidates. These results highlight the value of diversity-aware search for scientific discovery when available evaluators are informative but incomplete.

1. Introduction

Photolithography remains a central pattern-transfer technology in semiconductor manufacturing, where final pattern quality is determined by coupled materials and process factors including coating, baking, exposure, post-exposure reactions, and development (Dill et al., 1975; Mack, 2007; Ito, 2005). In particular, the development step strongly affects dissolution contrast, critical dimension control, line-edge roughness, residue formation, and pattern collapse (Brainard et al., 2004; Kim et al., 2010; Tate et al., 2014; Lian et al., 2024). As feature sizes shrink and process windows narrow, solvent and developer formulation design has become a high-dimensional materials discovery problem rather than a simple selection among standard commercial formulations (Tate et al., 2014; Lian et al., 2025).

Lithography solvent formulation design is inherently mixed discrete–continuous. A candidate formulation must select a small subset of solvents from a larger component pool and optimize their volume fractions while satisfying constraints on solubility, selectivity, volatility, miscibility, safety, and process compatibility. Hansen solubility parameters (HSPs), which decompose cohesive interactions into dispersion, polar, and hydrogen-bonding components, provide a useful physicochemical proxy for solvent–polymer affinity (Hansen, 2007; Tate et al., 2014). Recent studies further suggest that solubility-parameter-based representations and molecular simulations can support developer screening for photoresist materials (Lian et al., 2024; 2025). However, HSP-based metrics remain imperfect proxies: favorable predicted affinity does not fully determine downstream lithographic quality, which also depends on nonlinear resist–developer interactions, swelling, transport, latent image for-

---

[*]Equal contribution [1]State Key Laboratory for Novel Software Technology, Nanjing University, Nanjing, China [2]Suzhou Laboratory, Suzhou, China [3]Shanghai Artificial Intelligence Laboratory, Shanghai, China. Correspondence to: Tianfan Fu <futianfan@nju.edu.cn>, Ruzhi Zhang <zhangrz@szlab.ac.cn>.

mation, and process conditions (Mack, 2007; Ito, 2005; Kim et al., 2010).

This makes solvent discovery different from standard scalar optimization. Wet-lab validation is costly, candidate spaces are combinatorial, and available computational scores capture only part of the behavior that matters experimentally. Even when restricting the search to 50 candidate solvents and mixtures of 2 to 5 components, the discrete search space already contains millions of combinations before continuous mixing ratios are considered. In such settings, aggressively optimizing a proxy evaluator can drive search toward a narrow set of high-scoring templates, reducing the chance of discovering chemically distinct candidates that may perform well experimentally.

To effectively address these complex issues, we propose `LithographyAgent`, a diversity-aware neuro-symbolic search framework for lithography solvent discovery under imperfect evaluators. The framework decouples discrete and continuous decisions: LLMs serve as chemistry-informed hypothesis generators over solvent topologies, while a differentiable physics-informed module refines mixture ratios and enforces explicit feasibility constraints. To mitigate search collapse, `LithographyAgent` combines sibling-aware local diversification with memory-driven global planning. This design treats diversity as a structural property of the search process rather than as a post-hoc regularizer.

Empirically, `LithographyAgent` maintains 100% compliance with the explicit physicochemical constraints adopted in this work and increases exploration entropy from 3.53 to 4.37 relative to naive MCTS. Although this broader exploration trades off some short-term proxy-score performance, it uncovers formulations absent from baseline search trajectories under the same budget. We further compare against external search baselines under a shared physical ratio optimizer, including random feasible search, genetic search, MAP-Elites, surrogate-guided acquisition, and enumerative sampling. These baselines can achieve high physics-proxy scores, but their proxy-top candidates frequently fail EHS or process-feasibility screens, reinforcing the need to search for experimentally plausible diversity rather than only maximize a scalar proxy. Representative lithography experiments further suggest that candidates from these diverse regions can exhibit favorable qualitative pattern definition under the tested conditions.

Our contributions are:

- We formulate lithography solvent design as discovery under imperfect evaluators, where the goal is to surface feasible and diverse candidate sets rather than merely maximize a scalar proxy score.

- We introduce `LithographyAgent`, a neuro-symbolic framework that combines LLM-guided topology genera-

tion, differentiable physics-informed ratio optimization, and diversity-aware search.

- We provide external baseline, scoring-ablation, and calibration-ablation evidence showing that proxy-only optimization can select chemically implausible candidates, and that experimentally useful formulation discovery requires both physical refinement and process-aware calibration.

- We provide representative lithography validation, including quantitative CD-SEM measurements for two successful candidates and qualitative failure-mode analysis for additional candidates.

2. Related Work

2.1. LLM Agents and Search for Scientific Discovery

LLM-based agents have recently been used for scientific planning, tool use, chemical reasoning, and autonomous experimentation. Systems such as CHEMCROW (Bran et al., 2024), COSCIENTIST (Boiko et al., 2023), and domain-specific chemistry models such as CHEMLLM (Zhang et al., 2024) demonstrate that LLMs can coordinate external tools and support hypothesis generation in chemistry. Broader studies also suggest that LLMs can assist chemical reasoning, data handling, and tool-mediated scientific workflows (Jablonka et al., 2023).

In parallel, structured reasoning methods such as ReAct, Tree of Thoughts, Graph of Thoughts, RAP, and MCTS-style planning show that LLM generation can be improved by explicit search and feedback (Yao et al., 2023b;a; Besta et al., 2024; Hao et al., 2023). MCTS has also been successfully applied to chemical synthesis planning prior to the LLM era (Segler et al., 2018). However, most existing LLM-agent systems operate primarily in symbolic, procedural, or text-based spaces. They do not directly address mixed discrete–continuous formulation discovery under imperfect evaluators, where feasibility constraints and search diversity are both central.

2.2. Chemical Design under Proxy Objectives

Chemical design has long used optimization methods such as Bayesian optimization, evolutionary algorithms, reinforcement learning, deep generative models, and physics-informed machine learning (Frazier, 2018; Gómez-Bombarelli et al., 2018; Olivecrona et al., 2017; Popova et al., 2018; Karniadakis et al., 2021; Raissi et al., 2019). These approaches are useful for expensive black-box optimization or molecular generation, but formulation discovery introduces an additional difficulty: the available objective is often only a proxy for experimental value.

In lithography solvent design, HSP-based metrics and re-

lated physicochemical descriptors can guide screening, but they cannot fully capture downstream pattern quality. Our work therefore differs from pure score optimization. We treat diversity as a structural search requirement for robust discovery under evaluator uncertainty. This motivation is related to novelty search and quality-diversity optimization, which show that single-objective optimization can miss useful stepping stones and that diverse high-performing candidate sets can be more informative than a single best-scoring solution (Lehman & Stanley, 2011; Mouret & Clune, 2015; Pugh et al., 2016).

3. Problem Setup

Let $\mathcal{S} = \{s_1, \ldots, s_N\}$ be a candidate pool of $N = 50$ commercially available solvents. A formulation is defined as $(\mathcal{M}, \phi)$, where $\mathcal{M} \subset \mathcal{S}$ is a selected component set satisfying $2 \leq |\mathcal{M}| \leq 5$, and ϕ denotes volume fractions satisfying:

$$\sum_{i \in \mathcal{M}} \phi_i = 1, \quad \phi_i > 0. \tag{1}$$

The task is therefore mixed discrete–continuous: the system must choose both which solvents to include and how much of each solvent to use.

We use Hansen solubility parameters as the main physicochemical proxy for solvent–resist affinity. Each material is represented by a triplet $\delta = (\delta_d, \delta_p, \delta_h)$, corresponding to dispersion, polar, and hydrogen-bonding interactions. For a mixture, the effective HSP vector is computed by the linear mixing rule:

$$\delta_{\mathrm{mix}}(\phi) = \sum_{i \in \mathcal{M}} \phi_i \delta_i. \tag{2}$$

The HSP distance to a target material is:

$$R_a(\mathrm{mix}, \mathrm{target}) = \big[4(\delta_d^{\mathrm{mix}} - \delta_d^{\mathrm{target}})^2$$
$$+ (\delta_p^{\mathrm{mix}} - \delta_p^{\mathrm{target}})^2 \tag{3}$$
$$+ (\delta_h^{\mathrm{mix}} - \delta_h^{\mathrm{target}})^2\big]^{1/2}.$$

A smaller R_a indicates higher predicted affinity. The factor of 4 follows the standard anisotropic scaling convention in Hansen space (Hansen, 2007).

The computational evaluator combines target affinity, selectivity against a protective layer, and explicit feasibility constraints such as boiling-point hierarchy and flash-point safety. We emphasize that this evaluator is a proxy rather than a gold experimental metric. The goal is therefore not only to maximize its score, but to identify feasible, diverse, and experimentally promising candidates for downstream validation.

4. Method

4.1. Overview

`LithographyAgent` is a neuro-symbolic search framework that alternates between discrete formulation proposal, physics-constrained ratio refinement, candidate evaluation, and memory-guided planning. LLMs are used for discrete chemistry-informed hypothesis generation, while continuous mixture ratios are optimized by a differentiable physics module. This separation prevents the LLM from directly hallucinating numerical ratios and allows feasibility constraints to be enforced systematically.

At a high level, `LithographyAgent` performs tree-structured search over solvent topologies. Each expansion step proposes a discrete component set, optimizes its continuous ratios, evaluates the refined formulation, and stores the result in memory. The memory is then used to update future search directions, especially when the search begins to over-exploit a narrow family of high-scoring candidates.

4.2. LLM-Guided Discrete Search

The discrete search space is explored using a Monte Carlo Tree Search backbone (Browne et al., 2012). Each node represents a formulation topology and stores a compact state:

$$v = (a, r, n, Q), \tag{4}$$

where a denotes the proposed recipe topology, r the evaluation reward, n the visit count, and Q the running value estimate. Verbose reasoning traces are not stored at each node; instead, compact summaries are used to reconstruct the relevant path context during expansion.

During expansion, the LLM receives a concise summary of the path from the root to the current node and proposes a new solvent topology. The LLM is therefore used as a chemistry-informed generator rather than a numerical optimizer. It suggests plausible combinations of functional solvent roles, while the downstream physics module determines feasible mixture ratios.

4.3. Physics-Constrained Ratio Optimization

Given a proposed topology $\mathcal{M}$, the physics module optimizes the continuous volume fractions ϕ. We parameterize mixture ratios with softmax-normalized logits $\theta \in \mathbb{R}^{|\mathcal{M}|}$:

$$\phi_i = \frac{\exp(\theta_i)}{\sum_{j \in \mathcal{M}} \exp(\theta_j)}. \tag{5}$$

This enforces positivity and the simplex constraint by construction.

The optimization objective combines HSP-based target affinity, selectivity against the protective layer, and differentiable

Figure 1. Overview of `LithographyAgent`. The framework integrates LLM-based proposal generation, MCTS-based discrete search, differentiable physics-informed ratio refinement, and memory-guided diversity planning.

penalties for explicit physicochemical and engineering constraints:

$$\mathcal{L}_{\text{total}} = \mathcal{L}_{\text{affinity}} + \lambda_{\text{sel}}\mathcal{L}_{\text{selectivity}} \\ + \lambda_{\text{phys}}\mathcal{C}_{\text{phys}} + \lambda_{\text{sparse}}\mathcal{H}(\phi). \quad (6)$$

Here, $\mathcal{L}_{\text{affinity}}$ encourages affinity to the target resist, $\mathcal{L}_{\text{selectivity}}$ encourages separation from the protective layer, $\mathcal{C}_{\text{phys}}$ encodes explicit feasibility constraints, and $\mathcal{H}(\phi)$ is an entropy-based sparsity term that discourages unnecessary trace components.

After optimization, the recipe is rounded to practical increments, trace components are pruned, and the final formulation is rechecked against hard feasibility constraints. This post-processing step converts a continuous numerical optimum into a practical candidate recipe.

4.4. Diversity-Aware Local and Global Planning

Local sibling awareness reduces repeated proposals within the same branch. When expanding a node, the summaries of existing sibling proposals are injected as negative constraints. This encourages the LLM to generate chemically distinct alternatives rather than minor variants of previous candidates.

However, local diversification alone is insufficient when the evaluator favors a narrow family of high-scoring recipes. `LithographyAgent` therefore periodically summarizes historical candidates into a root-level global plan. The plan contains successful patterns, failure modes, risk warnings,

and underexplored directions. This memory-driven plan steers future search toward broader feasible regions, making diversity a structural property of the search process rather than a post-hoc regularizer.

4.5. Hybrid Evaluation and Search Update

Each refined candidate is evaluated by a stateless critic that combines physics-based compatibility with qualitative engineering assessment. The resulting reward is used for tree backpropagation and memory consolidation. Importantly, this reward is treated as a proxy rather than a fully reliable objective. For this reason, `LithographyAgent` is not designed to maximize critic agreement alone. Instead, its search dynamics preserve both feasibility and diversity under evaluator uncertainty.

5. Experiments

5.1. Experimental Setup

We evaluate `LithographyAgent` through external topology-search baselines, evaluator diagnostics, ratio-calibration analysis, representative lithography validation, and a final component ablation. For the main search and component-ablation experiments, we report three metrics:

- **Physical Validity (PV):** whether a candidate satisfies the explicit physicochemical constraints adopted in this work.

- **Top-10 Score:** the average score of the top 10 candidates

Figure 2. Diversity and distributional characteristics of generated formulations. `LithographyAgent` discovers more unique solvent topologies, achieves higher Shannon entropy, and reduces reliance on evaluator-favored dominant templates.

under the proxy evaluator.

- **Exploration Entropy:** Shannon entropy over unique discrete solvent topologies.

These metrics jointly measure feasibility, short-term proxy quality, and exploration diversity.

5.2. Diversity Analysis

Figure 2 further illustrates the effect of diversity-aware search. Sibling-aware expansion increases the number of unique solvent topologies by reducing local repetition. Global planning then changes the search distribution more substantially, encouraging exploration of underrepresented regions of the solvent space. These results support the central motivation of `LithographyAgent`: when the evaluator is imperfect, discovery should preserve multiple plausible candidate families rather than prematurely committing to a single high-scoring mode.

5.3. External Baselines with Shared Physics Optimization

To evaluate whether the LLM/MCTS search machinery is necessary, we add external topology-search baselines under the same downstream physics-informed ratio optimizer. Each method evaluates 150 solvent topologies per seed, corresponding to the same 10-round, 15-candidate budget used in the main search setting. The baselines include random feasible search, a genetic algorithm, MAP-Elites, a surrogate-guided acquisition baseline, and an enumerative sample. This comparison isolates the discrete search policy: all methods are given the same physical optimizer and are scored with the same proxy.

Because the physical proxy is not a wet-lab oracle, we also report offline engineering screens for EHS and process feasibility. These screens are not treated as experimental ground truth; instead, they indicate whether proxy-top candidates would be plausible candidates to spend wet-lab budget on. Table 1 shows the results across three seeds. The surrogate-guided baseline obtains the highest Top-10 physics-proxy score, but its Top-10 EHS pass rate is zero across all seeds.

Its overall EHS pass rate is also substantially lower than the other baselines. This supports our central claim: stronger proxy exploitation can drive search toward chemically implausible candidates, so the discovery objective should allocate budget toward feasible and diverse candidates rather than only toward proxy maximization.

5.4. Scoring and Calibration Diagnostics

We next diagnose two potential failure modes raised by the use of an LLM-involved evaluator. First, to test whether the LLM qualitative score simply reproduces the physics proxy ranking, we compare existing LLM critic scores with a physics-only RED-based score over 447 previously rated candidates. Table 2 shows weak rank correlation between physics-only and LLM-only scores and zero Top-10 overlap. This does not establish experimental validity, but it indicates that the qualitative critic is not a trivial restatement of the physical proxy.

Second, we evaluate how continuous ratio optimization is converted into experimentally specifiable recipes. Raw optimizer outputs are continuous and often contain trace components below the practical formulation grid. Table 3 compares raw physics ratios against 5% rounding, rule-based trace removal, and deterministic role-aware trace calibration. Raw continuous ratios fail the practical 5% ratio grid, whereas calibration converts them into specifiable recipes and substantially improves process feasibility. This supports the need for a calibration stage between differentiable physical optimization and wet-lab formulation.

5.5. Lithography Validation

Beyond proxy metrics, we conducted lithography validation under a fixed process flow to examine whether candidates discovered through diverse search could deliver experimentally promising pattern transfer. The validation used a 20 s development step after coating and exposure. The BARC layer was spin-coated at 1200 r for 25 s, followed by PR coating at 2000 r for 25 s. The samples were baked at 120°C for 60 s before exposure, exposed under 1.35 NA, 0.83/0.67 annular, XY-polarized illumination with exposure-energy setting 16, energy step 1, focus setting 0, and focus step 0.05, and then post-exposure baked at 120°C for 60 s.

This validation is intended as a limited prospective experimental panel rather than a full wet-lab benchmark. It tests whether representative candidates from the search process can produce measurable or visually distinguishable lithographic outcomes under a controlled process condition, while the large-scale algorithmic comparisons are handled by the offline baseline and diagnostic experiments above.

Figure 3 reports the experimentally recorded subset available for this revision. For #01, the image annotation gives

Table 1. **External baselines under the same physics-informed ratio optimizer.** Each run evaluates 150 solvent topologies; values are mean ± standard deviation over three seeds. Arrows indicate the preferred direction, and bold marks the best value in each metric. Process and EHS metrics are offline engineering screens rather than wet-lab ground truth.

Method	PV ↑	Top-10 Proxy ↑	Top-10 Process ↑	Top-10 EHS Pass ↑	Overall EHS Pass ↑	Process Accept. ↑
Random feasible search	0.86 ± 0.02	77.56 ± 0.69	$\mathbf{43.75 \pm 3.81}$	$\mathbf{0.17 \pm 0.05}$	0.54 ± 0.03	0.06 ± 0.01
Genetic algorithm	0.85 ± 0.02	78.39 ± 1.04	43.33 ± 9.07	0.13 ± 0.12	0.43 ± 0.03	0.07 ± 0.05
MAP-Elites	0.81 ± 0.03	77.03 ± 1.25	36.67 ± 1.23	0.07 ± 0.05	0.57 ± 0.04	0.07 ± 0.05
Surrogate-guided acquisition	$\mathbf{0.98 \pm 0.01}$	$\mathbf{80.66 \pm 1.34}$	37.33 ± 7.54	0.00 ± 0.00	0.12 ± 0.02	0.01 ± 0.01
Enumerative sample	0.78 ± 0.00	78.35 ± 0.00	39.00 ± 0.00	0.00 ± 0.00	$\mathbf{0.71 \pm 0.00}$	$\mathbf{0.08 \pm 0.00}$

Table 2. **Scoring ablation over 447 previously rated candidates.** This is a diagnostic for evaluator circularity and does not use wet-lab outcomes; unlike performance metrics, these diagnostic quantities are not assigned a monotonic optimization direction.

Metric	Value
Spearman(physics-only, LLM-only)	0.157
Spearman(physics-only, hybrid)	0.779
Spearman(LLM-only, hybrid)	0.667
Top-10 overlap: physics-only vs. LLM-only	0.00
Top-10 overlap: physics-only vs. hybrid	0.10
Top-10 overlap: LLM-only vs. hybrid	0.20
Top-20 overlap: physics-only vs. LLM-only	0.00

Table 3. **Offline ratio calibration ablation.** Raw continuous physics ratios are not directly specifiable on the 5% formulation grid; calibration converts them into practical recipes. Values are mean ± standard deviation across the five external topology-search sources. Arrows indicate the preferred direction, and bold marks the best value in each metric.

Variant	Practical ↑	Role ↑	Process ↑	Accept. ↑
Raw physics ratio	0.000 ± 0.000	0.304 ± 0.089	27.60 ± 5.31	0.000 ± 0.000
5% rounded physics ratio	$\mathbf{1.000 \pm 0.000}$	0.336 ± 0.104	46.43 ± 5.30	0.058 ± 0.029
Rule drop-trace calibration	$\mathbf{1.000 \pm 0.000}$	0.339 ± 0.106	46.47 ± 5.27	$\mathbf{0.060 \pm 0.030}$
Role-aware trace calibration	$\mathbf{1.000 \pm 0.000}$	$\mathbf{0.345 \pm 0.110}$	$\mathbf{47.60 \pm 5.16}$	0.056 ± 0.029

T35P125 with dose 12 mJ and focus -0.05, and reports CD 51.40 nm, LWR 3.27 nm, and LER 2.34 nm. For #02, the annotation gives T35P120 with dose 14 mJ and focus -0.05, and reports CD 56.01 nm, LWR 5.54 nm, and LER 3.83 nm.

The additional images provide a qualitative screen of lower-performing candidates and the commercial n-Butyl Acetate reference. Candidate #03 still shows a clear pattern, whereas #04 shows a clear pattern accompanied by swelling. Candidate #05 is shown for visual comparison. Candidate #06 preserves a clear alignment mark, but the line pattern is blurred. Because their overall development quality is visibly below that of #01 and #02, CD-SEM, LWR, and LER measurements were not performed for #03–#06 or for the commercial n-Butyl Acetate reference.

These observations highlight an important limitation of score-based evaluation: formulations with similar or even inferior theoretical scores can still yield more favorable ex-perimental behavior, while some high-scoring candidates can fail qualitatively.

Table 4 further illustrates the mismatch between proxy scores and qualitative experimental outcomes. Some high-scoring candidates produced poor lithographic behavior, supporting our premise that the evaluator should be treated as informative but incomplete. Pre-RED and Post-RED denote the RED values before and after formulation refinement.

A particularly informative case is the pair #02 and #15. They have identical Pre-RED, Post-RED, and proxy score values, yet their wet-lab outcomes differ sharply: #02 produced excellent patterning behavior, whereas #15 was qualitatively poor. This metric-degenerate contrast shows that the adopted proxy descriptors are useful but incomplete, and motivates preserving chemically diverse candidates instead of collapsing search onto a single high-scoring region.

We emphasize that these lithography experiments are preliminary. They are not intended as an exhaustive benchmark, but as concrete evidence that diversity-driven discovery can uncover experimentally promising formulations overlooked by score-centric search.

5.6. Component Ablation Study

Finally, we analyze the contribution of each internal component. Table 5 shows that the ReAct-Critic baseline achieves reasonable proxy scores but suffers from low physical validity due to unreliable numerical ratio generation. Adding the physics module raises PV to 100%, confirming the importance of decoupling discrete hypothesis generation from continuous ratio optimization.

However, Naive MCTS exhibits mode collapse. It achieves the highest Top-10 score, but repeatedly converges toward a narrow set of evaluator-preferred solvent templates. Sibling-aware expansion improves local diversity by discouraging redundant sibling proposals. The full `LithographyAgent` framework further increases entropy from 3.53 to 4.37 through memory-driven global planning.

The decrease in Top-10 score for `LithographyAgent` should not be interpreted simply as lower quality. Instead, it reflects a deliberate shift from short-term proxy-score

Table 4. Performance comparison of representative model-ranked candidates. Candidate IDs follow the experimental labels used throughout the lithography validation. Arrows indicate the preferred direction for scalar proxy metrics. Bold entries highlight high-scoring candidates with poor qualitative outcomes; #02 and #15 form a metric-degenerate pair with identical reported proxy descriptors but sharply different qualitative outcomes.

ID	Pre-RED ↓	Post-RED ↑	Perf.	Score ↑
#01	0.670	1.220	Excellent	85.25
#02	0.550	1.210	Excellent	84.00
#03	0.717	1.344	Subopt.	72.93
#04	0.673	1.278	Subopt.	75.13
#05	0.779	1.365	Good	74.65
#06	0.728	1.340	Good	80.30
#07	0.615	1.246	Good	78.28
#08	0.604	1.239	Good	80.50
#09	0.642	1.266	Good	78.10
#10	0.465	1.122	Good	78.93
#11	0.502	1.149	Good	78.68
#12	0.914	1.473	Good	78.85
#13	0.610	1.260	**Poor**	**86.25**
#14	0.630	1.250	**Poor**	**83.00**
#15	0.550	1.210	**Poor**	**84.00**

Table 5. **Evolutionary component ablation.** Impact of each component on constraint compliance, proxy-score quality, and exploration diversity under the same sampling budget. Arrows indicate the preferred direction, and bold marks the best value in each metric.

Method	Key Mechanism	PV ↑	Top-10 Score ↑	Entropy ↑	Dominant Failure Mode
ReAct-Critic Baseline	No special mechanism	Low	83.5	3.59	Unreliable numeric ratios
Naive MCTS	+ Physics module	100%	**86.5**	3.53	Mode collapse
MCTS + Sibling-Aware	+ Local diversification	100%	85.8	3.73	Redundant exploration
LithographyAgent (Ours)	+ Global planning	100%	81.17	**4.37**	No dominant failure mode

maximization toward broader exploration. Under imperfect evaluators, this trade-off is desirable because high proxy scores can correspond to repeated exploitation of evaluator-preferred templates rather than genuinely informative candidate discovery.

Figure 3. **Lithography validation images.** Top: quantitative CD-SEM measurements for #01 and #02. Bottom: qualitative development outcomes for #03–#06 and the commercial n-Butyl Acetate reference. Candidate labels are kept consistent across the experimental comparison.

6. Discussion and Limitations

This work argues that scientific formulation discovery should not always be framed as pure scalar optimization. In lithography solvent design, the computational evaluator is useful but incomplete: it captures selected physicochemical properties but cannot fully represent downstream pattern formation, swelling, transport, or process-dependent effects. Under such uncertainty, methods that aggressively optimize the proxy score may repeatedly exploit evaluator-preferred templates and miss chemically distinct candidates worth testing.

`LithographyAgent` addresses this issue by treating diversity as a structural property of the search process. Sibling-aware expansion reduces local redundancy, while memory-driven planning redirects global search toward underexplored feasible regions. The resulting framework trades some short-term proxy-score performance for broader candidate discovery, which is often more useful when wet-lab validation is expensive and the evaluator is imperfect.

Several limitations remain. First, the physics module relies on simplified surrogate constraints and does not capture all process-dependent effects relevant to real lithographic deployment. Second, the current wet-lab evidence should be interpreted as representative validation rather than a fully released quantitative benchmark: CD-SEM statistics are reported for the clearly resolved successful candidates, while lower-quality and failed cases are summarized qualitatively. Third, diversity-aware search can introduce variability across runs and still requires expert review, aggregation, and experimental validation.

These limitations clarify the intended role of `LithographyAgent`. The framework is not meant to replace chemists or provide definitive experimental judgments. Its role is to expand and organize the feasible candidate space so that downstream scientific decision-making can proceed from a stronger and more varied starting point.

7. Conclusion

We presented `LithographyAgent`, a diversity-aware neuro-symbolic framework for lithography solvent discovery under imperfect evaluators. By combining LLM-guided discrete hypothesis generation, differentiable physics-informed ratio optimization, sibling-aware local diversification, and memory-driven global planning, `LithographyAgent` preserves feasibility while expanding exploration beyond evaluator-favored templates. External baselines, evaluator diagnostics, calibration ablations, and representative lithography validation jointly suggest that diversity-aware, process-aware search can be more useful than proxy-score maximization alone when available

evaluators are informative but incomplete.

Acknowledgements

Jiangyu Chen, Zhou Zhang and Tianfan Fu are supported by Young Scientists Fund (C Class) of the National Natural Science Foundation of China (Grant No. 62506154), the Fundamental Research Funds for the Central Universities and Nanjing University International Collaboration Initiative (Grant No.020214380129) and the "111 Center" (No. B26023). The work described in this paper was also partially supported by the Research Grants Council of the Hong Kong SpecialAdministrative Region, China, under Project T45-401/22-N. We wish to express our sincere appreciation to Mr. Haoyang Wang, Dr. Runfeng Xu, Dr. Yisong Huo, Dr. Wentao Xu, Mr. Hang Shi, Ms. Yuhua Li, and all other team members for their support. Additionally, we acknowledge Dr. Xin Chen, Mr. Guodong Shen, Mr. Chunhua Chen, Mr. Kun Zhang, the AI and HTE project team for their valuable help. The completion of this article was made possible through their collective support and collaboration. The authors would also like to acknowledge the support from Key Technologies R&D Program of Jiangsu (No. BE2023095).

References

Besta, M., Blach, N., Kubicek, A., et al. Graph of thoughts: Solving complex reasoning tasks with graph-based prompting. In *Proceedings of the AAAI Conference on Artificial Intelligence*, volume 38, pp. 17682–17690, 2024.

Boiko, D. A., MacKnight, R., Kline, B., and Gomes, G. Autonomous chemical research with large language models. *Nature*, 624(7992):570–578, 2023.

Brainard, R. L., Trefonas, P., Lammers, J. H., Cutler, C., Mackevich, J., Trefonas, A., and Robertson, S. Shot noise, LER, and quantum efficiency of EUV photoresists. In *Emerging Lithographic Technologies VIII*, volume 5374, pp. 74–85. SPIE, 2004. doi: 10.1117/12.536411.

Bran, A. M., Cox, S., Schilter, O., Baldassari, C., White, A. D., and Schwaller, P. ChemCrow: Augmenting large-language models with chemistry tools. *Nature Machine Intelligence*, 6:525–535, 2024.

Browne, C. B., Powley, E., Whitehouse, D., Lucas, S. M., Cowling, P. I., Rohlfshagen, P., Tavener, S., Perez, D., Samothrakis, S., and Colton, S. A survey of monte carlo tree search methods. *IEEE Transactions on Computational Intelligence and AI in Games*, 4(1):1–43, 2012.

Dill, F. H., Hornberger, W. P., Hauge, P. S., and Shaw, J. M. Characterization of positive photoresist. *IEEE Transactions on Electron Devices*, 22(7):445–452, 1975.

Frazier, P. I. A tutorial on bayesian optimization. *arXiv preprint arXiv:1807.02811*, 2018.

Gómez-Bombarelli, R., Wei, J. N., Duvenaud, D., Hernández-Lobato, J. M., Sánchez-Lengeling, B., Sheberla, D., Aguilera-Iparraguirre, J., Hirzel, T. D., Adams, R. P., and Aspuru-Guzik, A. Automatic chemical design using a data-driven continuous representation of molecules. *ACS Central Science*, 4(2):268–276, 2018.

Hansen, C. M. *Hansen Solubility Parameters: A User's Handbook*. CRC Press, 2 edition, 2007.

Hao, S., Gu, Y., Ma, H., Hong, J. J., Wang, Z., Wang, D. Z., and Hu, Z. Reasoning with language model is planning with world model. In *Proceedings of the 2023 Conference on Empirical Methods in Natural Language Processing*, pp. 8154–8173, 2023.

Ito, H. Chemical amplification resists for microlithography. In *Microlithography/Molecular Imprinting*, volume 172 of *Advances in Polymer Science*, pp. 37–245. Springer, 2005. doi: 10.1007/b97574.

Jablonka, K. M., Ai, Q., Al-Feghali, A., Badhwar, S., Bocarsly, J. D., Bran, A. M., Bringuier, S., Brinson, L. C., Choudhary, K., Circi, D., et al. 14 examples of how LLMs can transform materials science and chemistry: A reflection on a large language model hackathon. *Digital Discovery*, 2(5):1233–1250, 2023.

Karniadakis, G. E., Kevrekidis, I. G., Lu, L., Perdikaris, P., Wang, S., and Yang, L. Physics-informed machine learning. *Nature Reviews Physics*, 3(6):422–440, 2021.

Kim, H.-W. et al. Dissolution behavior of photoresists: An in-situ analysis. *Journal of Photopolymer Science and Technology*, 23(5):639–644, 2010. doi: 10.2494/photopolymer.23.639.

Lehman, J. and Stanley, K. O. Abandoning objectives: Evolution through the search for novelty alone. *Evolutionary Computation*, 19(2):189–223, 2011.

Lian, P., Liu, Z., Hu, R., Yang, G., Yu, T., Chen, J., Li, Y., and Zeng, Y. Multiparameter method for developer screening of molecular glass resists via molecular simulations. *ACS Applied Materials & Interfaces*, 16(42):57636–57648, 2024. doi: 10.1021/acsami.4c11212.

Lian, P., Peng, R., Yu, T., Yang, G., Chen, J., Li, Y., and Zeng, Y. Molecular simulation-based developer screening for molecular glass photoresists. *Computational Materials Science*, 246:113429, 2025. doi: 10.1016/j.commatsci.2024.113429.

Mack, C. *Fundamental Principles of Optical Lithography: The Science of Microfabrication*. John Wiley & Sons, 2007.

Mouret, J.-B. and Clune, J. Illuminating search spaces by mapping elites. *arXiv preprint arXiv:1504.04909*, 2015.

Olivecrona, M., Blaschke, T., Engkvist, O., and Chen, H. Molecular de-novo design through deep reinforcement learning. *Journal of Cheminformatics*, 9(1):48, 2017.

Popova, M., Isayev, O., and Tropsha, A. Deep reinforcement learning for de novo drug design. *Science Advances*, 4 (7):eaap7885, 2018.

Pugh, J. K., Soros, L. B., and Stanley, K. O. Quality diversity: A new frontier for evolutionary computation. *Frontiers in Robotics and AI*, 3:40, 2016.

Raissi, M., Perdikaris, P., and Karniadakis, G. E. Physics-informed neural networks: A deep learning framework for solving forward and inverse problems involving nonlinear partial differential equations. *Journal of Computational Physics*, 378:686–707, 2019.

Segler, M. H. S., Preuss, M., and Waller, M. P. Planning chemical syntheses with deep neural networks and symbolic AI. *Nature*, 555(7698):604–610, 2018.

Tate, M. P., Cutler, C., Sakillaris, M., Kaufman, M., Estelle, T., Mohler, C., Tucker, C., and Thackeray, J. How to design a good photoresist solvent package using solubility parameters and high-throughput research. In *Advances in Resist Materials and Processing Technology XXXI*, volume 9051 of *Proceedings of SPIE*, pp. 90510R. SPIE, 2014. doi: 10.1117/12.2045974.

Yao, S., Yu, D., Zhao, J., Shafran, I., Griffiths, T. L., Cao, Y., and Narasimhan, K. Tree of thoughts: Deliberate problem solving with large language models. In *Advances in Neural Information Processing Systems*, volume 36, 2023a.

Yao, S., Zhao, J., Yu, D., Du, N., Shafran, I., Narasimhan, K. R., and Cao, Y. ReAct: Synergizing reasoning and acting in language models. In *International Conference on Learning Representations*, 2023b.

Zhang, D., Wei, W., Liu, Y., et al. ChemLLM: A chemical large language model. *arXiv preprint arXiv:2402.06852*, 2024.

A. Prompt Templates

This appendix reports the prompt templates used by `LithographyAgent`. The prompts are included to clarify how the LLM components are constrained: the LLM proposes discrete formulation hypotheses and qualitative critiques, while continuous ratio optimization and hard feasibility checks are handled by external tools and the physics module.

A.1. Formulation Advisor Prompt

A.1.1. ROLE DEFINITION

Role

You are the **Formulation Advisor**, appointed by the Materials Science Review Committee. Your responsibility is not to veto solutions, but to help the Generator identify risks and propose improvement suggestions.
Core Principle: Performance First, Perfection Second. Flawed but functional solutions may be accepted if their risks are explicit and manageable.

A.1.2. CORE TASKS

Step 1: Baseline Review.

Call `interface_recaller`, `audit_mixture_physics`, and `verify_mixture_performance`.
Check for **strictly prohibited** substances, limited to Benzene and Carbon Tetrachloride in the default setting. Other high-risk solvents may receive a **Yellow Warning (WARN)** when their predicted performance is strong, but they should not be rejected without justification unless the active strategy mode explicitly forbids them.

Step 2: Physical Assessment.

Solvency: The RED for S_{pre} must be < 1.0 as a hard constraint.
Protection: The RED for S_{post} should ideally be > 1.0. If it falls between 0.8 and 1.0, it can be treated as a **Conditional Pass**, provided the report gives a process-level justification, such as short development time.

A.1.3. SCORING DIMENSIONS

Dimension 1: Physical Performance, 5 points.

- **Excellent, 5 points**: $S_{pre} < 0.73$ and $S_{post} > 1.1$.

- **Pass, 3 points**: $S_{pre} < 1.0$ and $S_{post} \in [0.8, 1.0]$.

- **Fail, 0 points**: $S_{pre} > 1.0$.

Dimension 2: Engineering and Compliance, 5 points.

Apply deductions for engineering or compliance concerns:

- Toxic or high-risk solvent use: -1 point.

- Pseudo-mixture component below 5%: -1 point.

- No clear boiling-point gradient: -1 point.

A.1.4. OUTPUT FORMAT

Advisor Report Format

Formulation Evaluation Report

- **Conclusion**

  - Total Score: [0–10]

– Status: [Recommended / Feasible but Risky / Not Recommended]

- **Key Metrics**

  – Solvency (RED_Pre): [Value]
  – Protection (RED_Post): [Value]
  – EHS Risk: [None / Medium / High]

- **Improvement Suggestions**

  – Toxic solvent case: suggest safer alternatives for scale-up.
  – Low protection case: suggest shortening development time or increasing the protective-layer margin.

A.2. Principal Formulation Architect Prompt

A.2.1. ROLE DEFINITION

Role

You are a **Principal Formulation Architect**, trained under the guidance of leading experts in materials science. You command two sub-agents to collaborate on the **reverse design and engineering implementation** of photoresist developer formulations.
Core Philosophy:

- **Logic** > **Arithmetic**: Focus on qualitative screening using the relative spatial positions of Hansen Solubility Parameters (HSP), rather than attempting precise manual numerical computation.

- **Engineering** > **Theory**: Transform the mathematical optimum into an engineering solution suitable for manufacturing and experimental screening.

A.2.2. CORE OBJECTIVE

Objective

Design a developer that achieves:

- instant dissolution of S_{pre}, with **RED** < 1.0;

- protection of S_{post}, with **RED** > 1.0 whenever possible.

Target Layer (S_{pre}):

- Composition: 50% MadMA : 30% NLM : 20% HAdMA.

- HSP: $[18.27, 7.11, 8.20]$, $R_0 = 6.28$.

Protective Layer (S_{post}):

- Composition: 50% MAA : 30% NLM : 20% HAdMA.

- HSP: $[17.95, 11.47, 14.24]$, $R_0 = 8.81$.

A.2.3. DECISION LOGIC FRAMEWORK

Dimensional Analysis.

Focus on the **difference vector** rather than absolute distance alone.

- Compare δ_p and δ_h between S_{pre} and S_{post}.

- Identify the dominant separation dimension.

Example strategy: If S_{post} has significantly higher δ_h than S_{pre}, select solvents with lower δ_h to dissolve S_{pre} while reducing affinity to S_{post}.

Component Functional Positioning.

A formulation typically contains 1–3 functional roles:

- **Host solvent**: provides core solvency and is close to S_{pre} in HSP space.

- **Leverage solvent**: adjusts δ_p or δ_h to avoid S_{post}.

- **Modifier solvent**: improves process stability, often through boiling-point or volatility control.

A.2.4. HARD CONSTRAINTS AND ENGINEERING ADJUSTMENT

Physical and Compliance Constraints

- All components must be mutually miscible or experimentally justifiable.

- Strictly prohibited by default: Benzene and Carbon Tetrachloride.

- High-risk aromatic or regulated solvents, such as Toluene or Xylene, must be flagged and may be excluded under Green Mode.

- Prefer greener solvents, including esters, ketones, lactates, and glycol ethers when compatible with performance.

- Prefer a clear boiling-point gradient for process robustness.

Engineering Adjustment

The optimizer may output unrealistic ratios, such as $99.6\% : 0.4\%$. Apply engineering correction:

- Reject pseudo-mixtures with components in the 0.1%–5% range unless a trace role is explicitly justified.

- Remove non-essential trace components.

- Increase a functionally required minor component to 5%–10% if it is needed for stability or selectivity.

- Apply Occam's Razor: prefer a single solvent or a simpler mixture if it satisfies RED and safety requirements.

A.2.5. TOOL USAGE STRATEGY

- `get_dataset`: retrieve solvent library.

- `data-collector`: check miscibility, boiling point, and toxicity.

- `get_optimized_recipe`: obtain theoretical ratio; the ratio must still undergo engineering adjustment.

- `inspirer`: provide conceptual directions; do not directly copy existing formulations.

A.2.6. OUTPUT FORMAT

Solution Output Format

Recommended Solvent Mixture Solution

- **Recommended Combination**: [Solvent A] + [Solvent B]

- **Engineering Ratio, Post-Correction**

  - Solvent A: XX% (Role: Host, BP: XXX°C)

– Solvent B: XX% (Role: Modifier, BP: XXX°C)

- **Predicted Physical Indicators**

  – Mixture HSP: [...]
  – Solvency estimate: S_{pre} [Dissolves] / S_{post} [Protected]

- **Key Screening Logic**

  – Separation dimension: [...]
  – Formulation strategy: [...]

- **Miscibility and Compliance**: [...]

Prohibited Actions

- Do not provide copied existing formulations from literature.

- Do not use strictly prohibited solvents.

- Do not output ratios such as $99.5\% : 0.5\%$ as final engineering recipes.

- Do not output unverified formulations; final candidates must pass verification tools.

A.3. Global–Local Strategy Prompt

A.3.1. BASE STRATEGY PROMPT

Role

You are a **Director of Formulation R&D**, responsible for guiding formulation design at a strategic level. You do not perform direct formulation calculations. Instead, your role is to analyze historical experimental data and provide **high-level design strategies** to a downstream Generator Agent.
Your responsibility is to extract actionable insights from past experiments and translate them into structured design guidance.

A.3.2. INPUT DATA SPECIFICATION

You are provided with historical experimental records. Each record contains:

- **Formulation fingerprint**: solvent combinations.

- **Experimental results**: score and PASS/FAIL label.

- **Physical indicators**: including RED values.

- **Expert evaluation**: including EHS risks, physical defects, and process feedback.

A.3.3. CORE TASK AND REQUIRED OUTPUT

Analyze the provided data and produce a structured document titled **Next-Step Formulation Strategy Report**. This report will be used as the system-prompt prefix for the Generator Agent.
The report must contain four sections:

- **Proven Champions**: identify formulations with Score ≥ 9.0 and PASS; extract common structural patterns; provide refinement suggestions.

- **The Kill List**: identify failed or low-score formulations with Score < 6.0; list prohibited solvents; identify recurring failure patterns.

- **Yellow Flags**: identify moderately successful formulations with Score around 8.0; extract latent risks, such as boiling-point clustering; suggest mitigation strategies.

- **Exploration Vectors**: identify unexplored chemical regions and propose structured innovation directions.

A.3.4. STRATEGY MODE CONDITIONING

Dynamic Strategy Injection

In addition to the base prompt, a **strategy mode** is dynamically appended to guide the optimization direction. This enables a global–local search trade-off between exploitation and exploration.

Balanced Mode.

Objective: Achieve a balanced trade-off among solvency, protection, and engineering feasibility.

- Reuse high-performing formulation backbones with Score > 9.0.

- Fix known issues, such as lack of boiling-point gradient.

- Apply incremental improvements rather than drastic changes.

Innovation Mode.

Objective: Break path dependency and explore new chemical spaces.

- Prohibit the most frequently used dominant solvent in historical data.

- Focus on underexplored solvent classes, such as lactates and ethers.

- Accept slightly suboptimal RED values, such as 0.7–0.8, for exploration.

- Avoid minor ratio adjustments, such as $\pm 5\%$ tuning.

Green Mode.

Objective: Prioritize environmental, health, and safety compliance.

- Enforce strict exclusion of hazardous solvents.

- Prioritize green solvents, such as lactate esters, glycol ethers, and DBE.

- Allow moderate performance trade-offs for compliance.

Engineering Mode.

Objective: Ensure robustness in manufacturing and process stability.

- Enforce a clear boiling-point gradient, such as low–mid–high.

- Require S_{post} RED > 1.1 for a safety margin.

- Avoid pseudo-mixtures; all final components should be > 5% unless explicitly justified.

- Prefer simpler formulations with fewer components.

B. Solvent Library and Safety Evaluation

Table 6 reports the solvent pool used in this study, together with Hansen solubility parameters and qualitative safety or process-stability annotations. The table is placed in landscape orientation to keep the appendix single-column while preserving readability.

Table 6. Solvent properties and safety evaluation.

Name	SMILES	δ_d	δ_p	δ_h	Vapor Hazard	Bioacc.	Reactivity	Evap. Stability	Summary Evaluation
5-Methyl-2-hexanone	CC(C)CCC(C)=O	16.0	5.7	4.1	Medium	Medium	Medium	Medium	Medium hazard across all categories.
Acetone	CC(C)=O	15.5	10.4	7.0	Poor	Good	Good	Poor	High vapor hazard and poor evaporation stability; low bioaccumulation/reactivity.
Chloroform	ClC(Cl)Cl	17.8	3.1	5.7	Poor	Medium	Good	Poor	High vapor hazard and poor stability; low reactivity.
Isopropyl ether	CC(C)OC(C)C	13.7	3.9	2.3	Medium	Medium	Medium	Poor	Medium hazard; poor evaporation stability; use with caution.
Bromobenzene	c1ccc(cc1)Br	20.5	5.5	4.1	Poor	Medium	Good	Good	High vapor hazard; good stability and low reactivity.
Ethanol	CCO	15.8	8.8	19.4	Good	Good	Medium	Poor	Low hazard and bioaccumulation; poor evaporation stability.
2-Butanone (MEK)	CCC(C)=O	16.0	9.0	5.1	Medium	Good	Medium	Poor	Medium hazard; low bioaccumulation; poor stability.
Butyl benzoate	CCCCOC(=O)c1ccccc1	18.3	5.6	5.5	Good	Poor (High)	Good	Good	Low vapor hazard; high bioaccumulation risk; good stability.
Methyl n-amyl ketone	CCCCCC(C)=O	16.2	5.7	4.1	Good	Medium	Medium	Good	Low vapor hazard; moderate bioaccumulation; good stability.
Anisole	COc1ccccc1	17.8	4.1	6.7	Poor	Medium	Poor	Good	High vapor hazard and high reactivity; good stability.
Benzyl acetate	CC(=O)OCc1ccccc1	18.3	5.7	6.0	Good	Medium	Medium	Good	Low vapor hazard; moderate bioaccumulation; good stability.
1,2-Dichloroethane	ClCCCl	19.0	7.4	4.1	Poor	Medium	Good	Poor	High vapor hazard; low reactivity; poor stability.
Dichloromethane	ClCCl	18.2	6.3	6.1	Poor (High)	Medium	Good	Poor (High)	High vapor hazard; highly volatile; poor stability.
Trichloroethylene	ClC=C(Cl)Cl	18.0	3.1	5.3	Poor	Medium	Good	Poor	High vapor hazard; low reactivity; poor stability.
Ethyl acetate	CCOC(C)=O	15.8	5.3	7.2	Medium	Good	Good	Poor	Medium vapor hazard; low bioaccumulation; poor stability.
Cyclohexane	C1CCCCC1	16.8	0.0	0.2	Poor	Poor	Medium	Poor	High vapor hazard and high bioaccumulation; poor stability.
Acetonitrile	CC#N	15.3	18.0	6.1	Poor	Good	Good	Poor	High vapor hazard; low bioaccumulation; poor stability.
Isopropyl acetate	CC(C)OC(C)=O	14.9	4.5	8.2	Medium	Medium	Good	Poor	Medium hazard; low reactivity; poor stability.
Methanol	CO	15.1	12.3	22.3	Medium	Good	Good	Poor	Medium vapor hazard; low reactivity; poor stability.
n-Butyl acetate	CCCCOC(C)=O	15.8	3.7	6.3	Medium	Medium	Good	Medium	Moderate performance across all indicators.
Methylcyclohexane	CC1CCCCC1	16.0	0.0	1.0	Medium	Poor	Medium	Medium	Medium hazard; high bioaccumulation; moderate stability.
Methyl isobutyl ketone	CC(C)CC(C)=O	15.3	6.1	4.1	Poor	Medium	Poor	Medium	High vapor hazard and high reactivity; moderate stability.
n-Heptane	CCCCCCC	15.3	0.0	0.0	Medium	Poor	Medium	Poor	High bioaccumulation; poor evaporation stability.
Tetrachloroethylene	ClC(Cl)=C(Cl)Cl	18.3	5.7	0.0	Medium	Poor	Good	Medium	High bioaccumulation; low reactivity; moderate stability.
o-Xylene	Cc1ccccc1C	17.8	1.0	3.1	Good	Poor	Poor	Medium	Low vapor hazard but high bioaccumulation and reactivity.
m-Xylene	Cc1cccc(C)c1	17.4	1.0	3.1	Medium	Poor	Poor	Medium	High bioaccumulation and reactivity.
Isopropanol (IPA)	CC(C)O	15.8	6.1	16.4	Medium	Good	Good	Poor	Low bioaccumulation; low reactivity; poor stability.
Ethyl 3-ethoxypropionate	CCOCCC(=O)OCC	16.2	3.3	8.8	Good	Medium	Medium	Good	Low vapor hazard; moderate bioaccumulation; good stability.
n-Butanol	CCCCO	16.0	5.7	15.8	Medium	Good	Poor	Medium	Low bioaccumulation; high reactivity; moderate stability.
Toluene	Cc1ccccc1	18.0	1.4	2.0	Poor	Medium	Poor	Medium	High vapor hazard and high reactivity.
Ethyl ether	CCOCC	14.5	2.9	5.1	Poor	Good	Medium	Poor	High vapor hazard and poor stability.
1,3-Propanediol	OCCCO	16.8	13.5	23.2	Good	Good	Medium	Good	Excellent safety profile; low hazard; good stability.
N,N-Diethylacetamide	CCN(CC)C(=O)C	16.4	11.3	7.5	Medium	Good	Medium	Good	Low bioaccumulation; good evaporation stability.
2-Pentanone	CCCC(C)=O	16.0	7.6	4.7	Medium	Good	Poor	Medium	Low bioaccumulation; high reactivity; moderate stability.
Tetrahydrofuran (THF)	C1CCOC1	16.8	5.7	8.0	Poor	Good	Poor	Poor	High vapor hazard and reactivity; poor stability.
Benzyl alcohol	OCc1ccccc1	18.4	6.3	13.7	Good	Medium	Poor	Good	Low vapor hazard; high reactivity; good stability.
N,N-Dimethylformamide	CN(C)C=O	16.8	11.5	10.2	Medium	Good	Poor	Good	Low bioaccumulation; high reactivity; good stability.
1,4-Dioxane	C1COCCO1	19.0	1.8	7.4	Poor	Good	Medium	Medium	High vapor hazard; moderate stability.
gamma-Butyrolactone	O=C1CCCO1	19.0	16.6	7.4	Medium	Good	Good	Good	Low bioaccumulation and reactivity; good stability.
Diacetone alcohol	CC(C)(O)CC(C)=O	15.8	8.2	10.8	Good	Good	Good	Good	Excellent overall safety and stability profile.
Cyclohexanone	O=C1CCCCC1	17.8	6.3	5.1	Good	Good	Medium	Good	Low bioaccumulation; good evaporation stability.
2-Methylpyrazine	Cc1cnccn1	18.3	12.3	10.5	Poor	Medium	Poor	Medium	High vapor hazard and high reactivity.
N-Methylimidazole	Cn1ccnc1	19.7	15.6	11.2	Medium	Good	Poor	Good	Low bioaccumulation; high reactivity; good stability.
Ethyl lactate	CCOC(=O)C(C)O	16.0	7.6	12.5	Medium	Good	Medium	Good	Low bioaccumulation; good evaporation stability.
1,4-Butanediol	OCCCCO	16.6	15.3	21.7	Good	Good	Medium	Good	Low hazard; low bioaccumulation; good stability.
Diethanolamine	OCCNCCO	17.2	10.8	21.2	Medium	Good	Poor	Good	Low bioaccumulation; high reactivity; good stability.
Propylene glycol methyl ether	CC(O)COC	15.6	6.3	11.6	Medium	Good	Medium	Medium	Moderate performance across all safety indicators.
Dimethyl sulfoxide (DMSO)	CS(=O)C	18.4	16.4	10.2	Good	Good	Good	Good	Excellent safety profile; low hazard and high stability.
Methyl isobutyrate	COC(=O)C(C)C	15.1	3.7	6.3	Poor	Medium	Good	Poor	High vapor hazard and poor evaporation stability.
gamma-Valerolactone	CC1CCC(=O)O1	16.9	11.9	7.2	Medium	Good	Medium	Good	Moderate vapor hazard; good bioaccumulation and stability.
Water	O	15.5	16.0	42.3	Good	Good	Good	Poor	Low hazard/reactivity; poor evaporation stability.
Ethyl benzoate	CCOC(=O)c1ccccc1	18.2	5.4	6.0	Medium	Good	Good	Good	Low vapor hazard; low reactivity; good stability.
Phenethyl acetate	CC(=O)OCCc1ccccc1	18.2	5.3	6.1	Good	Medium	Good	Good	Low vapor hazard; low reactivity; good stability.
PGMEA	CC(=O)OCC(C)OC	15.6	5.5	7.3	Medium	Good	Good	Medium	Standard industrial solvent; moderate performance.
Methyl 3-ethoxypropionate	CCOCCC(=O)OC	16.1	3.6	8.6	Medium	Good	Good	Medium	Moderate vapor hazard; good safety profile.
Diglyme	COCCOCCOC	15.8	6.1	9.2	High	Low	Low	Medium	High vapor hazard (Reproductive toxicity); low reactivity.
n-Propyl lactate	CCCOC(=O)C(C)O	16.0	7.3	12.0	Low	Low	Medium	Good	Low bioaccumulation; good evaporation stability.
Methyl levulinate	CC(=O)CCC(=O)OC	17.5	9.0	8.5	Medium	Low	Medium	Good	Low bioaccumulation; good evaporation stability.
Proglyme	CC(OC)COC(C)COC	15.7	6.1	6.5	Low	Low	Low	Medium	Best Diglyme alternative; low toxicity P-series ether; inert; BP 175°C.
Ethylene glycol diacetate	CC(=O)OCCOC(C)=O	16.2	5.5	9.6	Low	Low	Medium	Good	HSP matches Diglyme closely; good leveling; eco-friendly high BP solvent.
2-Methyltetrahydrofuran	CC1CCCO1	16.9	5.0	6.3	Medium	Low	Medium	Medium	Bio-based green solvent; moderate volatility; good stability.
Butyl cellosolve	CCCCOCCO	16.4	6.3	13.7	High	Medium	Good	Medium	High vapor hazard (Reproductive toxicity); moderate bioaccumulation.
epsilon-Caprolactone	O=C1CCCCCO1	18.0	7.5	8.0	Medium	Medium	Medium	Medium	Moderate performance across all safety indicators.
Propylene carbonate	C1COC(=O)OC1C	18.2	13.0	9.0	Good	Good	Medium	Good	Low vapor hazard and bioaccumulation; good stability.

C. Hybrid Scoring Framework

To evaluate candidate developer formulations, we adopt a hybrid scoring framework that combines a physics-based metric with an LLM-based qualitative assessment. The total score is computed as

$$\text{Score}_{\text{total}} = 0.5 \, \text{Score}_{\text{physics}} + 0.5 \, \text{Score}_{\text{LLM}}. \tag{7}$$

The physics-based score captures thermodynamic compatibility, while the LLM-based score evaluates engineering feasibility and safety considerations.

C.1. Physics-Based Scoring

The physics-based score is derived from the RED values with respect to both the target layer S_{pre} and the protective layer S_{post}.

Solvency requirement for S_{pre}. A baseline score of 60 is assigned when

$$\text{RED}_{pre} = 0.70. \tag{8}$$

For every decrease of 0.01 in RED, the score increases by one point:

$$\text{Score}_{pre} = 60 + \frac{0.70 - \text{RED}_{pre}}{0.01}. \tag{9}$$

Protection requirement for S_{post}. A baseline score of 60 is assigned when

$$\text{RED}_{post} = 1.00. \tag{10}$$

For every increase of 0.01 in RED, the score increases by one point:

$$\text{Score}_{post} = 60 + \frac{\text{RED}_{post} - 1.00}{0.01}. \tag{11}$$

Combined physics score. The final physics score is computed as the average of solvency and protection:

$$\text{Score}_{\text{physics}} = \frac{\text{Score}_{pre} + \text{Score}_{post}}{2}. \tag{12}$$

C.2. LLM-Based Evaluation

The LLM-based score evaluates formulation quality from an engineering and practical perspective. It considers EHS risks, boiling-point distribution and gradient, thermodynamic plausibility of solvent mixtures, and functional roles of components. The LLM produces a holistic feasibility score reflecting robustness and manufacturability. This component is treated as a qualitative proxy, not as a ground-truth experimental metric.

D. Lithography Process and Measurement Details

In one embodiment, the photoresist solution was spin-coated onto a silicon wafer pre-treated with a bottom anti-reflective coating (BARC). The wafer was then pre-baked at $120°C$ for 60 s to yield a photoresist film with a thickness of approximately 100 nm. Exposure was performed using an ASML 1900Gi scanner with a 193 nm ArF light source and a numerical aperture of 1.35.

Following exposure, a post-exposure bake was conducted at $120°C$ for 60 s, followed by development using the tested developer formulation for 20 s. The resulting patterns were measured using a Hitachi CG6300 critical dimension scanning electron microscope. The preferred measurement parameters were: acceleration voltage of 400 V, probe current of 6.0 pA, magnification of 300K, and Linear detection mode. The detection area was set to 180 nm with 32 measurement points and a threshold of 45%.

D.1. Evaluation Criteria for Formulations #01–#15

The performance labels used in the main paper were assigned based on lithographic patterning results, including pattern visibility, pattern fidelity, and the presence of defects such as line collapse, bridging, or swelling under the corresponding process window.

Formulation #01 was evaluated at the T35P125 node under an exposure dose of 12 mJ/cm^2 and a focus setting of -0.05. Under these conditions, the measured critical dimension was 51.40 nm, the line width roughness was 3.27 nm, and the line edge roughness was 2.34 nm. Based on its pattern quality and quantitative metrics, formulation #01 was classified as *Excellent*.

Formulation #02 was evaluated at the T35P120 node under an exposure dose of 14 mJ/cm^2 and a focus setting of -0.05. The measured critical dimension was 56.01 nm, the line width roughness was 5.54 nm, and the line edge roughness was 3.83 nm. Based on the obtained lithographic performance, formulation #02 was also classified as *Excellent*.

For formulations #03 and #04, clear patterns could be observed at the T50P155 node. However, occasional line collapse was also present in the patterned features. These two formulations were therefore classified as *Suboptimal*.

For formulations #05–#12, the patterned images were generally distinguishable and relatively clear, indicating that development was successful to a certain extent. However, compared with formulations #03 and #04, these formulations exhibited more frequent defects, including line collapse, bridging, and swelling. These formulations were therefore classified as *Good*.

For formulations #13–#15, no clear lithographic patterns could be resolved after development, indicating unsuccessful pattern formation under the tested conditions. These formulations were therefore classified as *Poor*.

E. Solvent Diversity Metrics

To quantify the diversity of solvent usage across methods, we use Shannon entropy. For a dataset with n unique solvents, let c_i denote the occurrence count of solvent i, where $i = 1, 2, \ldots, n$. The relative frequency of solvent i is

$$p_i = \frac{c_i}{\sum_{j=1}^{n} c_j}. \tag{13}$$

The Shannon entropy H is

$$H = -\sum_{i=1}^{n} p_i \log_2 p_i, \tag{14}$$

with the convention $0 \log_2 0 = 0$. The entropy reaches its maximum $H_{\max} = \log_2 n$ when all solvents are used equally often. Lower entropy indicates a more concentrated usage pattern.

We also report two complementary metrics:

1. **Number of unique solvents** n: the number of distinct solvents appearing at least once.

2. **Top-k concentration ratio** C_k: the cumulative usage proportion of the k most frequently occurring solvents,

$$C_k = \frac{\sum_{i=1}^{k} c_{(i)}}{\sum_{j=1}^{n} c_j} \times 100\%, \tag{15}$$

where $c_{(i)}$ is the i-th largest occurrence count. We set $k = 5$.

Together, these metrics capture richness, uniformity, and concentration of solvent usage.

F. Algorithm and Complexity Analysis

F.1. Context Management and Computational Complexity

A fundamental limitation of applying standard LLM agents to long-horizon search is the growth of prompt length and attention cost. In a naive MCTS-style LLM agent, each node may retain the complete conversational history. For a search

---

Algorithm 1 `LithographyAgent`: Neuro-Symbolic Monte Carlo Tree Search

Require: Initial design objective x_{root}; maximum iterations T; maximum children per node K
Ensure: Best solvent formulation $(\mathcal{M}^*, \phi^*)$

1: Initialize root node v_0 with x_{root}
2: **for** $t = 1$ **to** T **do**
3:     *Selection phase*
4:     $v_{leaf} \leftarrow v_0$
5:     **while** v_{leaf} is fully expanded, i.e., $|\text{children}(v_{leaf})| \geq K$ **do**
6:         $v_{leaf} \leftarrow \arg\max_{c \in \text{children}(v_{leaf})} \left(\frac{Q(c)}{N(c)} + C\sqrt{\frac{\ln N(v_{leaf})}{N(c)}} \right)$
7:     **end while**
8:     *Sparse expansion and dynamic path reconstruction*
9:     $\mathcal{P} \leftarrow \text{TracePath}(v_0 \rightarrow v_{leaf})$
10:     $\mathcal{H}_{siblings} \leftarrow \text{SummarizeActions}(\text{children}(v_{leaf}))$
11:     $x_{input} \leftarrow \text{Concat}(\text{RootPlan}, \text{Summary}(\mathcal{P}), \text{NegativeConstraints}(\mathcal{H}_{siblings}))$
12:     $a_{new} \leftarrow \text{GeneratorMoE}(x_{input})$ {Discrete topology proposal}
13:     *Differentiable physics optimization*
14:     $\phi_{phys} \leftarrow \arg\min_\phi L_{hybrid}(a_{new}, \phi)$
15:     $(\mathcal{M}^*, \phi^*) \leftarrow \text{EngineeringReview}(a_{new}, \phi_{phys})$
16:     *Evaluation*
17:     $r \leftarrow \text{StatelessCritic}(\mathcal{M}^*, \phi^*)$
18:     Create node v_{new} storing $(\mathcal{M}^*, \phi^*, r, N = 0, Q = 0)$
19:     $\text{children}(v_{leaf}) \leftarrow \text{children}(v_{leaf}) \cup \{v_{new}\}$
20:     *Backpropagation*
21:     $v_{curr} \leftarrow v_{new}$
22:     **while** $v_{curr} \neq \text{NULL}$ **do**
23:         $N(v_{curr}) \leftarrow N(v_{curr}) + 1$
24:         $Q(v_{curr}) \leftarrow Q(v_{curr}) + r$
25:         $v_{curr} \leftarrow \text{Parent}(v_{curr})$
26:     **end while**
27:     *Memory consolidation*
28:     $\text{VectorDB.Store}(\mathcal{M}^*, \phi^*, r)$
29: **end for**
30: **return** $\text{GetBestSolution}(v_0)$

---

path of depth d and average interaction length L, the context required for a leaf node scales as $\mathcal{O}(dL)$, which can quickly exhaust the context window.

`LithographyAgent` reduces this burden through sparse state storage and dynamic path reconstruction. Each tree node stores only a lightweight semantic tuple, such as (a, r, n, Q), requiring $\mathcal{O}(1)$ storage per node. During expansion, the prompt is reconstructed from the root plan, compact path summaries, and sibling constraints. The resulting context length scales with summarized path information rather than full logs, approximately $\mathcal{O}(L_{root} + dL_{summary})$ with $L_{summary} \ll L$.

In implementation, the prompt can also be bounded by truncating or summarizing older path information. Thus, LLM inference cost per expansion depends on the bounded reconstructed prompt rather than the global size of the search tree. Continuous ratio optimization is handled by the physics module and scales as $\mathcal{O}(IE)$, where I is the number of gradient steps and E is the cost of evaluating the hybrid loss. This decoupling keeps the expensive LLM component focused on compact discrete hypothesis generation while delegating numerical feasibility to deterministic optimization.

G. Wet-lab Reporting Scope

Several formulation identities and exact ratios are reserved for follow-up journal and intellectual-property disclosure. The submitted version therefore reports wet-lab evidence at two levels: quantitative CD-SEM measurements for the disclosed successful candidates #01 and #02, and qualitative outcome labels for the broader representative set #01–#15. CD, LWR, and LER are reported only when the developed pattern is sufficiently resolved for meaningful measurement. For failed or visibly degraded cases, assigning CD statistics would be physically misleading; these cases are therefore summarized by qualitative outcome labels and representative SEM images when available.

The purpose of this wet-lab panel is not to serve as an exhaustive benchmark over all generated candidates. Instead, it provides prospective experimental evidence that the search can produce measurable lithographic patterns, while also showing that proxy-identical or high-scoring candidates can diverge sharply in downstream experimental behavior.